

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Pet. Corp.</i>		Lease <i>Wright J A</i>			Well # <i>4</i>	
Location of Well	Unit <i>1650N-W</i>	Section <i>34</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>	
Drilling Contractor <i>Lakue + Mearney</i>			Type of Equipment <i>Rotary to start 3-10-79</i>			
<u>APPROVED CASING PROGRAM</u>						
<i>* Witness</i>						
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement	
<i>9 7/8"</i>	<i>7"</i>	<i>20</i>		<i>1120</i>	<i>530 circ.</i>	
<i>6 1/4"</i>	<i>5 1/2 + 4 1/2</i>	<i>14 + 9.5</i>		<i>3150</i>	<i>175 "</i>	
Casing Data:						
<i>Int</i> <u>Surface</u> <i>29</i> joints of <u>7</u> inch <u>20</u> # Grade <u>K-SS</u>						
<input checked="" type="checkbox"/> (Approved) <input type="checkbox"/> (Rejected)						
Inspected by <u>mw</u> date <u>3/17/79</u>						
Cementing Program						
Size of hole <u>9 1/2</u> Size of Casing <u>7</u> Sacks cement required <u>500</u>						
Type of Shoe used <u>Guide Float collar</u> used <u>Insert</u> Btm 3 jts welded <u>Yes</u>						
TD of hole <u>1145</u> Set <u>1167</u> Feet of <u>7</u> Inch <u>20</u> # Grade <u>K-SS</u>						
New-used csg. @ <u>1145</u> with <u>150</u> sacks neat cement around shoe w/ <u>2% CC</u>						
+ <u>350</u> sax <u>Halliburton Lite</u> additives <u>5" Gilsinite</u> <u>4" Fb (c/c)</u> <u>3% CC</u>						
Plug down @ <u>9:45</u> (AM) <input checked="" type="checkbox"/> (PM) Date <u>3/17/79</u>						
Cement circulated <u>Yes</u> No. of Sacks <u>25</u> SX						
Cemented by <u>Halliburton</u> Witnessed by <u>MW</u>						
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____						
Casing test @ _____ (AM) (PM) Date _____						
Method Used _____ Witnessed by _____						
Checked for shut off @ _____ (AM) (PM) Date _____						
Method used _____ Witnessed by _____						
Remarks: <u>Centralizers + Baskets @ 270' + 780'</u>						
<u>Btm of Last Break 1037'</u>						