

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Coquina Oil Corp.</i>		Lease <i>Arkman State</i>		Well # <i>1</i>	
Location of Well	Unit <i>660 1980 W</i>	Section <i>27</i>	Township <i>19</i>	Range <i>25</i>	County <i>Elly</i>
Drilling Contractor			Type of Equipment <i>Rotary & start approx. 12-24-73</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>12 3/4</i>	<i>34.6</i>		<i>400</i>	<i>500 cwt.</i>
<i>11"</i>	<i>8 5/8</i> <i>9 5/8</i>	<i>29</i> <i>43.50</i>	<i>36"</i>	<i>1200</i>	<i>500 cwt.</i>
<i>7 7/8"</i>	<i>5 1/2</i>	<i>15.5-17</i>		<i>9600</i>	<i>400</i>

Casing Data:

Surface *34* joints of *9 5/8* inch # Grade *43.50* *36"* *32"*

J-55-K-55 - *1-40* (Approved) (Rejected)

Inspected by *J. A. Williams* date *1-16-74*

Cementing Program

Size of hole *12"* Size of Casing *9 5/8* Sacks cement required *600/sk*

Type of Shoe used *Guide* Float collar used *Insert* Btm *2* its welded

TD of hole *1200'* Set *1190* Feet of *9 5/8* Inch # Grade *J-K-55-4-40*

New-used csg. @ *1190* with *150* sacks neat cement around shoe and *2% cc 14.8*
+ *450/sk* *Howe-Lite* additives *1/4" # Floe 5# Gilsonite* *12.7"*

Plug down @ *7:45* (AM) (PM) Date *1-17-74*

Cement circulated *Yes* No. of Sacks *50/sk*

Cemented by *H. H. Hinton* Witnessed by *J. A. Williams*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *17 1/2" TD 400' RB st 390' 12 3/4 Guide shoe 10/sk*

450/sk Howe-Lite 100/sk Mene 2% cc Live 50/sk

1-10-74 34.60#