

28. Casing Record

Casing Size	Weight Lb./Ft.	Depth Set	Cementing Record
13-3/8"	48# H-40	328.16'	325 sx. C1 C 2% CaCl
9-5/8"	36# K-55, 32.30# H-40	2180'	100 sx. thick-set & 600 sx. hallite w/5# gilsonite & 1/4# flocel followed by 200 sx. C1 C 1/4# flocel w/2% CaCl
4-1/2"	N-80, K-55	9930'	490 sx. trinity lite, 5/10 of 1% CFR2 & 1/4# flocel/sx. 350 sx. C1 H with 5/10 of 1% CFR2 & 5# KCL/sx.