

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Exp. 10-11-85

Operator <u>Salkar, Inc.</u>		Lease <u>El Cheapo</u>		Well # <u>2</u>	
Location of Well	Unit <u>I</u>	Section <u>1</u>	Township <u>19</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor	<u>Salazar Bros.</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* 12 1/4	8 5/8	24 #		400	Circ
7 7/8	4 1/2	9 5 #		2200	200

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 100

Type of Shoe used Tex-Pat Float collar used Insert Btm 3 jts welded yes

TD of hole 404 Set 408 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 408 with 100 sacks neat cement around shoe

+ 400 sax Class A 2% CC additives

Plug down @ 1:30 (AM) (~~PM~~) Date 4-12-85

Cement circulated No No. of Sacks _____

Cemented by Dowell Witnessed by B. L. ...

Temp. Survey ran @ 1:00 (AM) (~~PM~~) Date 4-12-85 top cement @ 75

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by 1

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Run 1" to top of casing and cement to 107 5/8 class C