

Operator <i>Gates Petr Corp</i>		Lease <i>Parish IV Com</i>		Well # <i>2</i>	
Location of Well	Unit <i>F</i>	Section <i>26</i>	Township <i>19</i>	Range <i>24</i>	County <i>Eddy</i>
Drilling Contractor	<i>Undesignated</i>		Type of Equipment <i>Rotary</i>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>14 3/4</i>	<i>* 9 5/8</i>	<i>36# J-55</i>		<i>1300</i>	<i>900 Circ</i>
<i>8 3/4</i>	<i>7</i>	<i>26# N-80+ J-55</i>		<i>TD</i>	<i>As Warranted</i>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____ (Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <i>14 3/4"</i> Size of Casing <i>9 5/8"</i> Sacks cement required _____					
Type of Shoe used <i>guide</i> Float collar used <i>insert</i> Btm 3 jts welded <i>yes</i>					
TD of hole <i>1290'</i> Set <i>1290'</i> Feet of <i>9 5/8"</i> Inch <i>36</i> # Grade <i>J-55</i>					
New used csg. @ <i>1290'</i> with <i>200 270cc</i> sacks neat cement around shoe + <i>900</i> sax <i>Hall Lite</i> additives (<i>10# gilsonite, 1/2# floreal, 390cc</i>)					
Plug down @ <i>9:15</i> (AM) (PM) Date <i>12-18-89</i>					
Cement circulated <i>No</i> No. of Sacks <i>- 0 -</i>					
Cemented by <i>Halliburton</i> Witnessed by <i>Mike Stubblefield</i>					
Temp. Survey ran @ <i>9:15</i> (AM) (PM) Date <i>12-18-89</i> top cement @ <i>250'</i>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <i>* 1. Ran 1" tubing + tagged to c @ 228'</i> <i>cmt w/ 275 sx C I C</i> <i>Cement circulated to surface</i>					
Baskets @ <i>322'</i>			Last drly break @ <i>1103'</i>		