

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-27843

Operator <u>Yates Petr. Corp.</u>		Lease <u>Roy AET</u>		Well # <u>5</u>	
Location of Well	Unit <u>D</u>	Section <u>8</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36 #</u>		<u>1100</u>	<u>1000 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>23 # + 26 #</u>		<u>TD</u>	<u>1600 Circ</u>

Casing Data:

Surface _____ joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date _____

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 1069' Set 1069' Feet of 9 5/8" Inch 36 # Grade J-55

New-used csg. @ 1069' with 200 sacks neat cement around shoe

+ 800 sack Pacesetter Lite - C additives 10# gilsonite, 1/4# celoseal, 3% cc

Plug down @ 2:30 (AM) (PM) Date Feb. 24-94

Cement circulated No No. of Sacks - 0 -

Cemented by Western Company Witnessed by Mike Stubblefield

Temp. Survey ran @ 6:00 (AM) (PM) Date Feb. 24-94 top cement @ 100' *

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used + 200 ss thixsel-10#gil, 1/4#flosal, 3%cc Witnessed by _____

Remarks: * 1. Tag 700 @ 105' cement w- 100 ss c

2. Tag 700 @ 105' cement w- 75 ss c

3. Tag 700 @ 90' cement w- 200 ss c + 8 yds pea gravel

4. Tag 700 @ 90' cement w- 150 ss c

Ready-mixed well to surface from 90'

L.D.B. - 940'