

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

2/17/84

Operator <u>YPC</u>		Lease <u>CITDEL 7G</u>		Well # <u>1</u>	
Location of Well	Unit <u>A</u>	Section <u>36</u>	Township <u>20S</u>	Range <u>27E</u>	County <u>Eddy</u>
Drilling Contractor	<u>LMZ</u>		Type of Equipment <u>ROTARY</u>		

APPROVED CASING PROGRAM

*** WITNESS**

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2</u>	<u>13 3/8</u>	<u>2 "</u>	<u>NEW</u>	<u>2550</u>	<u>CIRC</u>
<u>* 12 1/4</u>	<u>8 5/8</u>	<u>24-28 #</u>	<u>"</u>	<u>2500</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>17-20 #</u>	<u>"</u>	<u>TD</u>	<u>650 SX.</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used TEX PT Float collar used insert Btm 3 jts welded yes

TD of hole 2390 Set 2390 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 2390 with 250 sacks neat cement around shoe 3% CaCl₂

+ 550 sax HALLIBURTON additives 10 # GUM NITE, 5 # FIOCELE, 3 % CaCl₂

Plug down @ 2:15 (AM) (PM) Date 3-17-84

Cement circulated yes No. of Sacks 355xs.

Cemented by HALLIBURTON Witnessed by Randy Brooks

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____