

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28435

Operator <i>Marathon Oil Co.</i>		Lease <i>N. Indian Basin Ut</i>		Well # <i>18</i>	
Location of Well	Unit <i>J</i>	Section <i>2</i>	Township <i>21</i>	Range <i>23</i>	County <i>Eddy</i>
Drilling Contractor <i>NA</i>			Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>30"</i>	<i>16"</i>	<i>Cond.</i>		<i>60'</i>	<i>Redimix Surf</i>
<i>14 3/4"</i>	* <i>9 5/8"</i>	<i>36 #</i>		<i>1250'</i>	<i>1400 Surf</i>
<i>8 3/4"</i>	<i>7"</i>	<i>23#, 26 #</i>		<i>8000'</i>	<i>1100 Surf</i>

Casing Data:

Surface _____ joints of *9 5/8"* inch *36* # Grade _____

(Approved) (Rejected)

Inspected by *M.S.* date *5-18-95*

Cementing Program

Size of hole *14 3/4"* Size of Casing *9 5/8"* Sacks cement required _____Type of Shoe used *guide* Float collar used *Insert* Btm 3 jts welded *y-c*TD of hole *1255'* Set *1255'* Feet of *9 5/8"* Inch *36* # Grade *J-55*(New)-used csg. @ *1255'* with *250* sacks neat cement around shoe+ *550 sk* *Pacette L.P.* additivesPlug down @ *6:00* (AM) (PM) Date *5-16-95*Cement circulated *No* No. of Sacks *-0-*Cemented by *Western Co.* Witnessed by *Mike Stubb/field*Temp. Survey ran @ *12:00* (AM) (PM) Date *5-16-95* top cement @ *100' +* *

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *+ 200 sk thick set** 1. Tag loc @ *140'* cmt *6/25 sk* c.l.c.2. Tag loc @ *90'* cmt *u/50 sk* c.l.c. cement circ. to surface.*14 3/4" hole R.T. - 72 hours**Wtr @ 650'*