

CEMENT

<u>TYPE OF STRING</u> <u>INTERVAL (FT)</u> <u>FROM-TO TYPE MIX</u>	<u>GEL %</u>	<u>SALT %</u>	<u>CaCl2</u>	<u>SLURRY</u> <u>WEIGHT</u> <u>LB./CF</u>	<u>SLURRY</u> <u>YIELD</u> <u>CF/SCK</u>	<u>TOTAL AMT.</u> <u>REQUIRED</u> <u>SCK/CF</u>	<u>FILL UP</u>	<u>BHT</u>	<u>SIZE</u>	<u>REMARKS</u>
(L) 11900-14625								2050	6 1/2"	
Class "H"		5#/sk KCL		15.6	118	(325) 383	11900			50% excess. Add 8/10 of 1 Halad 22 and 4/10 of 1% CF

Cement to be batch mixed. Mixing tests to be run 5-6 days before setting depth reached. Cement volumes will be recalculated from log caliper.