Form 3160-5 (August 1999)

Approved By

Conditions of approval, if any, are attached. Approval of this notice does not warrant or certify that the applicant holds legal or equitable title to those rights in the subject lease which would entitle the applicant to conduct operations thereon.

## **UNITED STATES** DEPARTMENT OF THE INTERIOR **BUREAU OF LAND MANAGEMENT**

**SUNDRY NOTICES AND REPORTS ON WELLS** Do not use this form for proposals to drill or to re-enter an

FORM APPROVED
OMB NO. 1004-0135
Expires: November 30, 2000

NMSF079004	
6. If Indian, Allottee or Tribe Name	

Date 08/16/2004

abandoned wei	i. Use form 3160-3 (AP	ט) tor such proposals.	0,	
SUBMIT IN TRII	PLICATE - Other instruc	ctions on reverse side.	7. If Unit or CA/A NMNM78424	greement, Name and/or No.
1. Type of Well			8. Well Name and	
Oil Well Gas Well Oth	ner		SAN JUAN 32	-8 221A
Name of Operator     CONOCOPHILLIPS COMPAN	Contact:	"JUANITA FARRELL E-Mail: juanita.r.farrell@cond	9. API Well No. 30-045-3240	6-00-X1
3a. Address PO BOX 2197 WL3 6054 HOUSTON, TX 77252		3b. Phone No. (include area Ph: 505.599.3419 Fx: 505.599.3442		, or Exploratory TLAND COAL
4. Location of Well (Footage, Sec., 7	., R., M., or Survey Descriptio	n)	11. County or Pari	sh, and State
Sec 9 T31N R8W SWNW 211	15FNL 670FWL		SAN JUAN C	COUNTY, NM
12. CHECK APPE	ROPRIATE BOX(ES) To	O INDICATE NATURE (	OF NOTICE, REPORT, OR OTI	HER DATA
TYPE OF SUBMISSION		ТҮР	E OF ACTION	
Nicking of Intent	☐ Acidize	Deepen	Production (Start/Resume)	Water Shut-Off
□ Notice of Intent	Alter Casing	Fracture Treat	Reclamation	☐ Well Integrity
Subsequent Report	Casing Repair	☐ New Construction	Recomplete	Other Drilling Operations
Final Abandonment Notice	☐ Change Plans	Plug and Abando	n Temporarily Abandon	Drilling Operations
	Convert to Injection	Plug Back	☐ Water Disposal	
Attach the Bond under which the wo following completion of the involved testing has been completed. Final Al determined that the site is ready for f Casing was set in this well pe	rk will be performed or provid loperations. If the operation rebandonment Notices shall be final inspection.)  r attached wellbore sche	e the Bond No. on file with BLN esults in a multiple completion o led only after all requirements, i	neasured and true vertical depths of all p 1/BIA. Required subsequent reports shar recompletion in a new interval, a Form including reclamation, have been completed.	ll be filed within 30 days 3160-4 shall be filed once
14. Thereby certify that the foregoing is	Electronic Submission For CONOCOP	#34580 verified by the BLM HILLIPS COMPANY, sent to ssing by ADRIENNE BRUML	Well Information System of the Farmington LEY on 08/16/2004 (04AXB3178SE)	
Name (Printed/Typed) JUANITA	FARRELL	Title AU	THORIZED REPRESENTATIVE	
Signature (Electronic	Submission)	Date 08/	13/2004	
	THIS SPACE F	OR FEDERAL OR STA	TE OFFICE USE	
Approved By ACCEPT	ED		ENNE BRUMLEY OLEUM ENGINEER	Date 08/16/200

Title 18 U.S.C. Section 1001 and Title 43 U.S.C. Section 1212, make it a crime for any person knowingly and willfully to make to any department or agency of the United States any false, fictitious or fraudulent statements or representations as to any matter within its jurisdiction.

Office Farmington

## ConocoPhillips

## **END OF WELL SCHEMATIC**

Spud   2-Aug-04
Release Drl Rig: 5-Aug-04   Move In Cav Rig:
Move In Cav Rig:    Tubing Head   Release Cav Rig:     Tubing Head   Release Cav Rig:
SurfaceCement   Date cmt'd:   2-Aug-04     Lead:   150 sx Class G Cement   + 2%   BWOC S001 CaCl2   + 0.25   lb/sx D130 Cellophane Flakes   1.16 cuft/sx, 174 cuft slurry at 15.8 ppg     Displacement:   15.3 bbls fresh wtr   Bumped Plug at:   10:43 hrs w/ 330 psi   Final Circ Press:   150 psi @ 0.6 bpm   Returns during job:   YES   CMT Returns to surface:   15 bbls
SurfaceCement   Date cmt'd:
SurfaceCement   Date cmt'd:
Date cmt'd: 2-Aug-04  Lead: 150 sx Class G Cement  + 2% BWOC S001 CaCl2  + 0.25 lb/sx D130 Cellophane Flakes  1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
Date cmt'd: 2-Aug-04  Lead: 150 sx Class G Cement  + 2% BWOC S001 CaCl2  + 0.25 lb/sx D130 Cellophane Flakes  1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
Lead: 150 sx Class G Cement  + 2% BWOC S001 CaCl2  + 0.25 lb/sx D130 Cellophane Flakes  1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
+ 2% BWOC S001 CaCl2 + 0.25 lb/sx D130 Cellophane Flakes  1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
+ 0.25 lb/sx D130 Cellophane Flakes  1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
1.16 cuft/sx, 174 cuft slurry at 15.8 ppg  Displacement: 15.3 bbls fresh wtr  Bumped Plug at: 10:43 hrs w/ 330 psi  Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
Displacement: 15.3 bbls fresh wtr Bumped Plug at: 10:43 hrs w/ 330 psi Final Circ Press: 150 psi @ 0.6 bpm Returns during job: YES CMT Returns to surface: 15 bbls
Bumped Plug at: 10:43 hrs w/ 330 psi Final Circ Press: 150 psi @ 0.6 bpm Returns during job: YES CMT Returns to surface: 15 bbls
Final Circ Press: 150 psi @ 0.6 bpm  Returns during job: YES  CMT Returns to surface: 15 bbls
Returns during job: YES CMT Returns to surface: 15 bbls
CMT Returns to surface: 15 bbls
Floats Held: No floats used
1 10415 1 1014.
W.O.C. for 6.00 hrs (plug bump to start NU BOP)
W.O.C. for 11.25 hrs (plug bump to test csg)
Intermediate Cement
Date cmt'd: 5-Aug-04
Lead: 430 sx Class G Cement
+ 3% D079 Extender
+ 0.25 lb/sx D029 Cellophane Flakes
+ 0.2% D046 Antifoam
+ 0.05 gal/sx D047 Antifoam
2.61cuft/sx, 1070.1 cuft slurry at 11.7 ppg
Tail: 100 sx 50/50 POZ: Class G cement
+ 2% D020 Bentonite
+ 2% S001 Calcium Chloride
+ 5 lb/sx D024 Gilsonite
+ 0.25 lb/sx D029 Cellophane Flakes
+ 0.1% D046 Antifoam
1.27 cuft/sx, 127 cuft slurry at 13.5 ppg
Displacement: 130.7 bbls
Bumped Plug at: 03:11 hrs w/ 1450 psi
Final Circ Press: 800 psi @ 0.7 bpm
Returns during job: YES
CMT Returns to surface: 20 bbls
Floats Held: X Yes No

TURBOLIZERS @ 2331', 2287, & 2244'.