

UNITED STATES
DEPARTMENT OF THE INTERIOR
BUREAU OF LAND MANAGEMENT

FORM APPROVED
OMB NO. 1004-0135
Expires: November 30, 2000

SUNDRY NOTICES AND REPORTS ON WELLS
Do not use this form for proposals to drill or to re-enter an abandoned well. Use form 3160-3 (APD) for such proposals.

SUBMIT IN TRIPLICATE - Other instructions on reverse side.


1. Type of Well <input type="checkbox"/> Oil Well <input checked="" type="checkbox"/> Gas Well <input type="checkbox"/> Other		5. Lease Serial No. NMSF078278
2. Name of Operator CONOCOPHILLIPS COMPANY		6. If Indian, Allottee or Tribe Name
3a. Address P O BOX 2197 WL 6106 HOUSTON, TX 77252		7. If Unit or CA/Agreement, Name and/or No. NMMN78416B
3b. Phone No. (include area code) Ph: 832.486.2463		8. Well Name and No. SAN JUAN 29-6 UNIT 90F
4. Location of Well (Footage, Sec., T., R., M., or Survey Description) Sec 15 T29N R6W NENE 400FNL 400FEL 36.73185 N Lat, 107.44212 W Lon		9. API Well No. 10-63907623-00-X1 39-27623
		10. Field and Pool, or Exploratory BASIN DAKOTA BLANCO MESAVERDE
		11. County or Parish, and State RIO ARRIBA COUNTY, NM

12. CHECK APPROPRIATE BOX(ES) TO INDICATE NATURE OF NOTICE, REPORT, OR OTHER DATA

TYPE OF SUBMISSION	TYPE OF ACTION			
<input checked="" type="checkbox"/> Notice of Intent	<input type="checkbox"/> Acidize	<input type="checkbox"/> Deepen	<input type="checkbox"/> Production (Start/Resume)	<input type="checkbox"/> Water Shut-Off
<input type="checkbox"/> Subsequent Report	<input type="checkbox"/> Alter Casing	<input type="checkbox"/> Fracture Treat	<input type="checkbox"/> Reclamation	<input type="checkbox"/> Well Integrity
<input type="checkbox"/> Final Abandonment Notice	<input type="checkbox"/> Casing Repair	<input type="checkbox"/> New Construction	<input type="checkbox"/> Recomplete	<input checked="" type="checkbox"/> Other
	<input type="checkbox"/> Change Plans	<input type="checkbox"/> Plug and Abandon	<input type="checkbox"/> Temporarily Abandon	Change to Original A
	<input type="checkbox"/> Convert to Injection	<input type="checkbox"/> Plug Back	<input type="checkbox"/> Water Disposal	PD

13. Describe Proposed or Completed Operation (clearly state all pertinent details, including estimated starting date of any proposed work and approximate duration thereof. If the proposal is to deepen directionally or recompleat horizontally, give subsurface locations and measured and true vertical depths of all pertinent markers and zones. Attach the Bond under which the work will be performed or provide the Bond No. on file with BLM/BIA. Required subsequent reports shall be filed within 30 days following completion of the involved operations. If the operation results in a multiple completion or recompleat in a new interval, a Form 3160-4 shall be filed once testing has been completed. Final Abandonment Notices shall be filed only after all requirements, including reclamation, have been completed, and the operator has determined that the site is ready for final inspection.)

ConocoPhillips is requesting to change the cement calculations from the original APD. Attached is a copy of the revised cement calculations from Schlumberger.



14. I hereby certify that the foregoing is true and correct. Electronic Submission #51854 verified by the BLM Well Information System For CONOCOPHILLIPS COMPANY, sent to the Farmington Committed to AFMSS for processing by ADRIENNE BRUMLEY on 12/20/2004 (05AXB0513SE)	
Name (Printed/Typed) CHRIS GUSTARTIS	Title AUTHORIZED REPRESENTATIVE
Signature (Electronic Submission)	Date 12/14/2004

THIS SPACE FOR FEDERAL OR STATE OFFICE USE

Approved By <u>Jim Lovato</u>	Title <u>Petr. Eng</u>	Date <u>12/21/04</u>
Conditions of approval, if any, are attached. Approval of this notice does not warrant or certify that the applicant holds legal or equitable title to those rights in the subject lease which would entitle the applicant to conduct operations thereon.		Office

Title 18 U.S.C. Section 1001 and Title 43 U.S.C. Section 1212, make it a crime for any person knowingly and willfully to make to any department or agency of the United States any false, fictitious or fraudulent statements or representations as to any matter within its jurisdiction.

**** BLM REVISED ** BLM REVISED ** BLM REVISED ** BLM REVISED ** BLM REVISED ****

NMOCD

5 L B

San Juan 29-6 # 90F

SURFACE CASING :

Drill Bit Diameter	12.25"	
Casing Outside Diameter	9.625"	Casing Inside Diam. 9.001"
Casing Weight	32.3	ppf
Casing Grade	H-40	
Shoe Depth	230'	
Cement Yield	1.16	cuft/sk
Excess Cement	125	%
Cement Required	148	sx

SHOE 230', 9.625", 32.3 ppf, H-40 STC

INTERMEDIATE CASING :

Drill Bit Diameter	8.75"	
Casing Outside Diameter	7"	Casing Inside Diam. 6.456"
Casing Weight	20	ppf
Casing Grade	J-55	
Shoe Depth	3931'	
Lead Cement Yield	2.72	cuft/sk
Lead Cement Excess	150	%
Tail Cement Length	786.2'	
Tail Cement Yield	1.31	cuft/sk
Tail Cement Excess	150	%
Lead Cement Required	418	sx
Tail Cement Required	233	sx

SHOE 3931', 7", 20 ppf, J-55 STC

PRODUCTION CASING :

Drill Bit Diameter	6.25"	
Casing Outside Diameter	4.5"	Casing Inside Diam. 4.000"
Casing Weight	11.6	ppf
Casing Grade	N-80	
Top of Cement	3731'	200' inside intermediate casing
Shoe Depth	8161'	
Cement Yield	1.44	cuft/sk
Cement Excess	50	%
Cement Required	465	sx

SHOE 8161', 4.5", 11.6 ppf, N-80 LTC

San Juan 29-6 # 90F			
	Surf. Csg	Int. Csg	Prod. Csg
OD	9.625	7	4.5
ID	9.001	6.456	4.000
Depth	230	3931	8161
Hole Diam	12.25	8.75	6.25
% Excess Lead		150	
% Excess Tail	125	150	50
Lead Yield		2.72	
Tail Yield	1.16	1.31	1.45
Ft of Tail Slurry	230	786.2	4430
Top of Tail Slurry	0	3144.8	3731
Top of Lead Slurry	N/A	0	N/A
Mud Wt (ppg)	8.9	9.0	air drill
Mud Type	WBM	WBM	air drill

Surface Casing						
	Ft	Cap	XS Factor	bbls	cuft	sx
Open Hole Annulus	230	0.055804	2.25	27.2	153.0	131.9
Shoe Track Volume	42	0.078735	1	3.3	18.6	16.0
Total				30.6	171.5	147.9

Intermediate Casing						
	Ft	Cap	XS Factor	bbls	cuft	sx
Lead Open Hole Annulus	2914.8	0.026775	2.5	195.1	1095.5	402.7
Lead Cased Hole Annulus	230	0.031104	1	7.2	40.2	14.8
Lead Total				202.3	1135.6	417.5
Tail Open Hole Annulus	786.2	0.026775	2.5	52.6	295.5	225.6
Tail Shoe Track Volume	42	0.04049	1	1.7	9.5	7.3
Tail Total				54.3	305.0	232.8

Production Casing						
	Ft	Cap	XS Factor	bbls	cuft	sx
Open Hole Annulus	4230	0.018275	1.5	116.0	651.0	449.0
Cased Hole Annulus	200	0.020818	1	4.2	23.4	16.1
Total				120.1	674.4	465.1

San Juan 29-6 # 90F		
9-5/8 Surface Casing		
Cement Recipe	Class G Standard Cement	
	+ 3% S001 Calcium Chloride	
	+0.25 lb/sx D029 Cellophane Flakes	
Cement Volume	148	sx
Cement Yield	1.16	cuft/sx
Cement Volume	171.5	cuft
Cement Density	15.8	ppg
Water Required	4.983	gal/sx
Compressive Strength		
Sample cured at 60 deg F for 8 hrs		
12 hrs	1174	psi
36 hrs	2763	psi

San Juan 29-6 # 90F

7" Intermediate Casing		
Lead Slurry		
Cement Recipe	Class G Standard Cement	
	+0.25 lb/sx D029 Cellophane Flakes	
	+ 3% D079 Extender	
	+ 0.20% D046 Antifoam	
	+ 10 lb/sx Pheno Seal	
Cement Required	418	sx
Cement Yield	2.72	cuft/sx
Slurry Volume	1135.6	cuft
	202.3	bbls
Cement Density	11.7	ppg
Water Required	15.74	gal/sx
Compressive Strength		
Sample cured at 140 deg F for 24 hrs		
2 hr 37 min	50	psi
39 hr 40 min	500	psi

7" Intermediate Casing		
Tail Slurry		
Cement Slurry	50 / 50 POZ: Class G Standard Cement	
	+0.25 lb/sx D029 Cellophane Flakes	
	+ 2% D020 Bentonite	
	+ 1.5 lb/sx D024 Gilsonite Extender	
	+ 2% S001 Calcium Chloride	
	+ 0.10% D046 Antifoam	
	+ 6 lb/sx Pheno Seal	
Cement Required	238	sx
Cement Yield	1.31	cuft/sx
Slurry Volume	305.0	cuft
	54.3	bbls
Cement Density	13.5	ppg
Water Required	5.317	gal/sx
Compressive Strength		
Sample cured at 140 deg F for 24 hrs		
24 hr	908	psi
48 hr	1950	psi

San Juan 29-6 # 90F		
4-1/2" Production Casing		
Cement Recipe	50 / 50 POZ:Class G Standard Cement	
	+0.25 lb/sx D029 Cellophane Flakes	
	+ 3% D020 Bentonite	
	+ 1.0 lb/sx D024 Gilsonite Extender	
	+ 0.25% D167 Fluid Loss	
	+ 0.15% D065 Dispersant	
	+ 0.1% D800 Retarder	
	+ 0.1% D046 Antifoamer	
	+ 3.5 lb/sx PhenoSeal	
Cement Quantity	465	lb/sx
Cement Yield	1.45	cuft/sx
Cement Volume	674.4	cuft
	120.1	
Cement Density	13	ppg
Water Required	6.47	gal/sx
Compressive Strength		
Sample cured at 200 deg F for 24 hrs		
6 hr 35 min	500	psi
24 hr	2373	psi