



# *Cole Production Co.*

---

(505) 325-1415  
P.O. Box 191  
3001 Northridge Dr.  
Farmington, New Mexico 87499

JACK A. COLE

MARCUS NO. A 16

## CASING AND CEMENT SUMMARY

9-29-86

TD-5750'. Ran 141 joints  $4\frac{1}{2}$ ", 10.50 lb., K-55 casing, measured 5757.41, set at 5769.41 KB.

Cemented first stage through float collar at 5716.66' with 10 bbls. mud flush followed by 425 sacks (612 cu. ft.), 50-50 pozmix, 2% Gel,  $6\frac{1}{4}$  lbs. Gilsonite and 6 lbs. salt per sack. Plug down 12:45 A.M. 10-10-86. Calculated top of cement 3611.41' KB. Circulate  $3\frac{1}{2}$  hours between stages.

Cemented second stage through stage collar at 2304.48 with 10 bbls. mud flush followed by 300 sacks, (687 cu. ft.) 65-35 pozmix, 12% Gel and  $6\frac{1}{2}$  lbs. Gilsonite per sack, followed by 50 sacks (59 cu. ft.) Class "B" cement. Plug down 5:28 A.M. 10-10-86. Circulated 5 bbls. cement to surface.