

## SUNDRY NOTICES AND REPORTS ON WELLS

1. oil well ☒ gas well ☐ other ☐

Jack A. Cole

P.O. Box 191, Farmington, N.M. 87499

AT SURFACE: 870' FNL, 1740' FWL

AT TOP PROD. INTERVAL: *Same*

AT TOTAL DEPTH: Same

TEST WATER SHUT-OFF	<input type="checkbox"/>
FRACTURE TREAT	<input type="checkbox"/>
SHOOT OR ACIDIZE	<input type="checkbox"/>
REPAIR WELL	<input type="checkbox"/>
PULL OR ALTER CASING	<input type="checkbox"/>
MULTIPLE COMPLETE	<input type="checkbox"/>
CHANGE ZONES	<input type="checkbox"/>
ABANDON*	<input type="checkbox"/>
(other)	

X

BUREAU OF LAND MANAGEMENT  
FARMINGTON RESOURCE AREA

RECEIVED

OCT 16 1986 (N)

(NOTE: Report results of multiple completion or zone change on Form 9-330.)

17. DESCRIBE PROPOSED OR COMPLETED OPERATIONS (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work. If well is directionally drilled, give subsurface locations and measured and true vertical depths for all markers and zones pertinent to this work.)\*

See Attached for Casing and Cement Summary

Subsurface Safety Valve: Manu. and Type \_\_\_\_\_ Set @ \_\_\_\_\_ Ft.

18. I hereby certify that the foregoing is true and correct

## Production

SIGNED Douglas B. Baker TITLE Superintendent DATE October 15, 1986

(This space for Federal or State office use)

APPROVED BY \_\_\_\_\_  
CONDITIONS OF APPROVAL IF ANY:

TITLE

DATE \_\_\_\_\_

**NMOCC**

# *Cole Production Co.*

---

(505) 325-1415  
P.O. Box 191  
3001 Northridge Dr.  
Farmington, New Mexico 87499

JACK A. COLE

MARCUS NO. A 16

## CASING AND CEMENT SUMMARY

9-29-86

TD-5750'. Ran 141 joints  $4\frac{1}{2}$ ", 10.50 lb., K-55 casing, measured 5757.41, set at 5769.41 KB.

Cemented first stage through float collar at 5716.66' with 10 bbls. mud flush followed by 425 sacks (612 cu. ft.), 50-50 pozmix, 2% Gel,  $6\frac{1}{4}$  lbs. Gilsonite and 6 lbs. salt per sack. Plug down 12:45 A.M. 10-10-86. Calculated top of cement 3611.41' KB. Circulate  $3\frac{1}{2}$  hours between stages.

Cemented second stage through stage collar at 2304.48 with 10 bbls. mud flush followed by 300 sacks, (687 cu. ft.) 65-35 pozmix, 12% Gel and  $6\frac{1}{2}$  lbs. Gilsonite per sack, followed by 50 sacks (59 cu. ft.) Class "B" cement. Plug down 5:28 A.M. 10-10-86. Circulated 5 bbls. cement to surface.