

Cement report for the 7" casing.

Float shoe was set at 4530'. A DV tool was set at 2770'.
1st stage cement was 155 sx, 50/50 poz + 6% gel lead slurry
and 100 sx class "B" + $\frac{1}{4}$ # flocele tail slurry. Circulation
was lost $\frac{1}{2}$ way through 1st stage.

2nd stage was cemented with 278 sx class "B". Cement did
not circulate

Casing was perforated at 1328' - 1322' with 4 shots. Pumped
50 sx class "B". Had good circulation to surface.

