

1. NAME OF OPERATOR
Yates Drilling Company

2. ADDRESS OF OPERATOR
207 South 4th Street, Apt. 104, N.M. 88210

3. LOCATION OF WELL (Report location clearly and show well with log. State right of way, if any. See also space 17 below.)
At surface
2285' FSL & 2055' FEL

14. PERMIT NO.

15. WELLBORE'S (Show whether 11, 12, or 22)

6727' GR

16. NAME OF WELL

Gillespie Federal

17. WELL NO.

1

18. FIELD AND ZONE, OR VICINITY

Wildcat

19. T, R., M., OR BLM, AND
COUNTY OR AREA

Section 29-T23N-R8W

20. COUNTY OR PARISH 21. STATE

San Juan

N.M.

16. Check Appropriate Box To Indicate Nature of Notice, Report, or Other Data

NOTICE OF INTENTION TO:

RE-ENTRY REPORT OF:

TEST WATER SHUT-OFF

FIELD WATER CLOSING

WATER SHUT-OFF

REPAIRING WELL

FRACTURE TREATMENT

REPAIRING CEMENT

FRACTURE TREATMENT

ALTERING CASING

REPAIRING CASING

ABANDON

REPAIRING OR ABANDONING

REPAIRMENT

REPAIR WELL

CHANGE PLANT

(OTHER) Production Casing

X

(Other)

(Note: Report only if of multiple completion on well. Completion or Re-Entry Report and Log form)

17. DESCRIBE WORK DONE OR COMPLETED. (Describe all pertinent details and give pertinent facts, including estimated date of starting any proposed work. If well is permanently plugged give subsurface locations and measured and true vertical depths for all markers and zones pertinent to this work.)

1-8-86 San 120 joints of 4 1/2' 9.5# J-55 STAC casing set at 4896.70'. 1-Cement Type Guide shoe set 4897.70'. Orifice fill collar set 4897'. DV tool set 3781'. Cemented in two stages, as follows: Stage #1: Pumped 10 bbls. water, 10 bbls. chemical wash and 15 bbls water ahead of cement. Cemented with 250 sacks BW-V with 6 1/4#/sx. D-42, 167 BW-V-walt and 1/4#/sx. Collofolates. Compressive strength of cement - 1500 psi in 12 hours. PD 8:15 AM 1-9-86. Pumped plug to 1000 psi, relieved pressure and float held okay. Pumped opening 1/2". Pumped DV tool and cemented to pin. Mud did get thin for approx. 4 ribs. Stage #2: Pumped 10 bbls. water, 10 bbls. chemical wash and 15 bbls water ahead of cement. Cemented with 575 sacks BW-V + 6 1/4#/sx. Collofolates, 1/4#/sx. Collofolates. Topped in with 50 sacks Class "B" + 24 Class "C" + 1/4#/sx. Collofolates. Compressive strength of cement - 1500 psi in 12 hours. PD 12:45 AM 1-9-86. Pumped plug to 1000 psi, relieved pressure, float held okay. Cement did not simulate. A.C.

Circulated 45 sx cmt to surface, per Toby Rhodes, Yates

Drly

RECEIVED

JAN 24 1986

ENV. DIV.

JAN 14 1986

18. I hereby certify that the foregoing is true and correct

(Signature of Operator)

TITLE

APPROVED BY

TITLE

DATE

(Signature of Operator)

*See Instructions on Reverse Side

NMOCC