

DISTRICT I
P.O. Box 1980, Hobbs, NM 88240

DISTRICT II
P.O. Drawer DD, Artesia, NM 88210

DISTRICT III
1000 Rio Brazos Rd., Aztec, NM 87410

OIL CONSERVATION DIVISION
P.O. Box 2088
Santa Fe, New Mexico 87504-2088

WELL API NO.
30-045-27870

5. Indicate Type of Lease
STATE ☒ FEE ☐

6. State Oil & Gas Lease No.
VA-143

SUNDRY NOTICES AND REPORTS ON WELLS
(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A
DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT"
(FORM C-101) FOR SUCH PROPOSALS.)

1. Type of Well:
OIL WELL ☐ GAS WELL ☒ OTHER

2. Name of Operator
Giant Exploration & Production Company

3. Address of Operator
P.O. Box 2810, Farmington, N.M. 87499

4. Well Location
Unit Letter N : 990 Feet From The South Line and 1650 Feet From The West Line
Section 32 Township 25N Range 12W NMPM San Juan County

10. Elevation (Show whether DF, RKB, RT, GR, etc.)
6249' GR

11. Check Appropriate Box to Indicate Nature of Notice, Report, or Other Data

NOTICE OF INTENTION TO:

PERFORM REMEDIAL WORK ☐ PLUG AND ABANDON ☐
TEMPORARILY ABANDON ☐ CHANGE PLANS ☐
PULL OR ALTER CASING ☐
OTHER: OIL CON. DIV. DIST. 3 ☐

SUBSEQUENT REPORT OF:

REMEDIAL WORK ☐ ALTERING CASING ☐
COMMENCE DRILLING OPNS. ☐ PLUG AND ABANDONMENT ☐
CASING TEST AND CEMENT JOB ☐
OTHER: Drilling Progress ☒

12. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

Drilled out from under casing with 7-7/8" bit. Drilled to TD of 830'. Ran Compensated Density-Neutron logs with gamma ray. Log tops as follows: Fruitland - 676', Upper Basal Fruitland Coal - 865', Pictured Cliffs - 945'. Ran 20 jts. (856.89') of 5-1/2", 15.5#, K-55, 8rd, LT&C casing. BakerLoked cement nosed guide shoe on bottom and insert float valve on top of shoe jt. Ran centralizers on tops of 1st, 3rd, 5th, 7th, and 9th jts. Casing set at 828.10', PBD at 785.86'. Cemented casing as follows: Mixed and pumped 70 sks. (144.2 cu. ft.) Class "B" cement containing 2% Thriftyment and 1/4#/sk. cellophane flakes. Tailed in with 100 sks. (118 cu. ft.) of Class "B" cement containing 2% CaCl2 and 1/4#/sk. cellophane flakes. Cement circulated to surface. Pressure tested casing to 3500 psi for 15 minutes. Test ok. Waiting on completion operations.

I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNATURE Aldrich L. Kuchera TITLE President

TYPE OR PRINT NAME Aldrich L. Kuchera

DATE OCT 8 1990

TELEPHONE NO.

(This space for State Use)

Original Signed by FRANK T. CHAVEZ

APPROVED BY _____ TITLE _____ DATE _____

CONDITIONS OF APPROVAL, IF ANY:

OCT 04 1990