

13 3/8" Surface - 240 Sks. of Class "B" cement w/1/4# gel-flake/sk. and 3% calcium chloride. 283 cu. ft.

9 5/8" Intermediate Casing - 290 Sks. of 65/35 Class "B" Pozmix w/6% gel and 2% calcium chloride, 1/2 cu. ft. Perlite, followed by 100 sks. of Class "B" w/2% calcium chloride, 1/2 cu. ft. of Perlite. 623 cu. ft.

7" Liner - 480 Sks. of 50/50 Class "B" Pozmix w/2% gel, 0.6% Halad 9, 6.25# Gilsonite plus 1/4# Flocele/sk. 667 cu. ft.

4 1/2" Liner - 90 Sks. of Class "B" w/8% gel, 1/4 cu. ft. fine Gilsonite/sk. and 0.4% HR-7, followed by 100 Sks. of Class "B" w/1/4# fine Tuf-plug/sk. and 0.4% HR-7. 297 cu. ft.

