

CEMENT RECORD

8 5/8" SURFACE CASING

325 SKS CLASS 'B', 2% CALCIUM
CHLORIDE.

CIRCULATED TO SURFACE

5 1/2" PRODUCTION CASING

CEMENTED IN THREE STAGES:

1st. 230 SKS CLASS 'B' 50/50 POZ
, 6% GEL, 2# MED TUF
PLUG P/SK. FOLLOWED W/100 SKS
CLASS 'B' NEAT.

2nd. 312 SKS CLASS 'B' 65/35 POZ, 6%
GEL, 2# MED TUF PLUG P/SK.
FOLLOWED W/100 SKS CLASS 'B'
NEAT.

3rd. 127 SKS CLASS 'B' 65/35 POZ
6% GEL, 2# MED TUF PLUG P/SK.
FOLLOWED W/100 SKS CLASS 'B'
NEAT.

CIRCULATED TO SURFACE

