

B. & R. SERVICE, INC.

TEMPERATURE SURVEY

COMPANY.....DELHI-TAYLOR OIL CORPORATION.....
WELL.....STOREY #1.....FIELD.....
COUNTY.....SAN JUAN.....STATE.....NEW MEXICO.....
SEC.....TWP.....RGE.....

APPROX. TOP CEMENT.....1985'

Survey Begins at.....4500.....Ft. Ends at.....5600.....Ft.

Approx. Fill-Up.....OVER 100%.....Max. Temp.....116°

Log Measured From.....ROTARY FLOOR.....Run No.....

Casing Size	Casing Depth	Diam of Hole	Depth
5 1/2" from	to 7730	7 7/8" from	to
from	to	from	to

Date of Cementing.....SEPTEMBER 21, 1960.....Time.....11:15 P.M.

Date of Survey.....SEPTEMBER 25, 1960.....Time.....3:00 A.M.


Amount of Cement.....200 SACKS.....Type.....REGULAR

Amount of Admix.....50/50 CONE 1, 4% GEL, 12# GILSONITE/SK+75 SKLATEX

Recorded by.....DOV HOLLOWAY.....Witnessed by.....D.E. MITCHELL

REMARKS OR OTHER DATA

1ST D.V. TOOL @ 5545'



TEMPERATURE IN DEGREES FAHRENHEIT

