

Production (liner):

Preflush	20 bbl.	Chemical Wash	
	20 bbl.	Fresh water	
Lead Cement		360 sx 50/50 Class "B"/Poz	493 cu.ft.
Slurry 1		+ 2% gel (extender)	
TOC @		+ 5 #/sk Kolite (lost circulation add.)	
(50' above TOL)		0.4% Fluidloss Additive	
		+1/4 #/sk. Cellophane Flake	

Slurry Properties:	Density		Water
	(lb/gal)	(ft3/sk)	(gal/sk)
Slurry 1	13.5	1.37	6.3

Liner Float Equipment: Float Shoe and Float Collar (furnished by Liner Hanger Company)
1 Thread Lock Compound

Note:

1. Coordinate w/Liner hand to drop plug, or set/release Liner as required
2. The job should be pumped at 5-6 bpm max rate. Do not exceed 4 bpm on displacement
3. Wash pump and lines before displacement. Slow to 3 bpm for the last 30 bbl of displacement.
4. This is to be a rigless completion. After cement set time, liner top will be dressed off an liner circulated clean with 2 % KCl or 2 gal/1000 gal L64.

+