

Cement Program

8 5/8" casing → 350 SK Class "B" Neat cement, 2% CaCl₂, Circ. to Surface
4 1/2" " → 1st 400 SK Class "B" Neat cement, 50:50 POZ, 6% gel,
2* Mod. tuf plug, .2% friction reducer, 100 SK
Class "B" Neat cement.
→ 2nd 1289 SK Class "B" Neat cement, 50:50 POZ, 6% gel,
1/2 ft³ peroxide, .2% friction reducer, .8% fluid
loss additive, 100 SK class "B" Neat cement. Circ. to Surface
2 7/8" liner → 275 SK Class "B", 50:50 POZ, 6% gel, 75 SK Class "B" Neat