*						
Form 3160-5 (June 2015) DI B	UNITED STATES EPARTMENT OF THE INTERIOR HOBBS OCD UREAU OF LAND MANAGEMENT				OMB N Expires: J	APPROVED VO. 1004-0137 January 31, 2018
SUNDRY NOTICES AND REPORTS ON WELLS N 2 9 2017 Do not use this form for proposals to drill or to re-enter an abandoned well. Use form 3160-3 (APD) for such proposals.					5. Lease Serial No. NMNM40406 6. If Indian, Allottee or Tribe Name	
1. Type of Well ☐ Gas Well ☐ Ot			8. Well Name and No. HAMON FED COM & 6H			
2. Name of Operator LEGACY RESERVES OPER/	SON		9. API Well No. 30-025-43214			
			. (include area code) 9-5200 Ext: 520			
4. Location of Well (Footage, Sec., 7	11. County or Parish, State					
Sec 6 T20S R34E SWSE 579		LEA CO COUNTY, NM				
12. CHECK THE A	PPROPRIATE BOX(ES)	TO INDICA	TE NATURE O	F NOTICE,	REPORT, OR OTI	HER DATA
TYPE OF SUBMISSION	TYPE OF ACTION					
Notice of Intent	□ Acidize	Dee Dee	pen	Product	tion (Start/Resume)	□ Water Shut-Off
□ Subsequent Report	□ Alter Casing	Hydraulic Fracturing		□ Reclamation		U Well Integrity
			Construction	-	Recomplete Other	
Final Abandonment Notice	Change Plans	Plug Plug	and Abandon	n 🗖 Temporarily Abandon		
Legacy Reserves Operating re intermediate casing cement p utilizing two DV tools. Both DV shoe and a minimum of 200 fe placement. Please see the fol	rocedures. This option wo / tools shall be set a minir eet above the current sho	uld allow for num of 50 fee e and adjust o	a three-stage ce et below the prev cement proportio	ment job /ious casing nately base	d on	
14. I hereby certify that the foregoing is	Electronic Submission #3	379692 verifie	d by the BLM We	II Information	n System	
Name (Dring JTrue J) MATT DI	RATING LP, sent					
Name (Printed/Typed) MATT DICKSON			Title DRILLI	NG ENGINE	ER	
Signature (Electronic Submission)			Date 06/23/2017			
	THIS SPACE FO	DR FEDERA	L OR STATE	OFFICE U	SE	
Approved By			Title			Date
Conditions of approval, if any, are attached. Approval of this notice does not warrant or certify that the applicant holds legal or equitable title to those rights in the subject lease which would entitle the applicant to conduct operations thereon.			Office			
itle 18 U.S.C. Section 1001 and Title 43 States any false, fictitious or fraudulent					ake to any department or	agency of the United
Instructions on page 2) ** OPERA	TOR-SUBMITTED ** O	PERATOR-	SUBMITTED *	* OPERAT	OR-SUBMITTED	** KZ

Hamon #6H

Intermediate Casing

-

In the event that circulation is lost (> 50%) while drilling the 12-1/4" intermediate hole in the Capitan Reef at +/-4000', we will plan to install a DV tool and external casing packer within 200' of the top depth where lost circulation occurred and will pump a two-stage cement job with the potential to add an additional DV tool for a three-stage cement job. If there is no lost circulation a single stage cementing procedure will be followed. Legacy plans to cement to surface regardless of whether a single stage, 2-stage or 3-stage procedure is implemented.

No DV tool (80% excess on lead & 80% excess on tail to design for cement top at surface)

Lead: 1400 sx (35:65) poz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0.25% bwoc FL- 52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

<u>Tail:</u> 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

With (1) DV Tool (100% excess on lead & 100% excess on tail to design for cement top at surface)

Assuming DV tool set at 3950' but if the setting depth changes, cement volumes will be adjusted proportionately.

Stage 1

Lead: 400 sx (35:65) paz (fly ash) class C cement+ 4% bwoc Bentonite II+ 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Stage 2

Lead: 1100 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

<u>Tail:</u> 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

With (2) DV Tools (100% excess on lead & 100% excess on tail to design for cement top at surface)

Assuming one DV tool set at 3950' and one DV tool set at 1800' but if the setting depths change, cement volumes will be adjusted proportionately.

Stage 1

Lead: 400 sx (35:65) paz (fly ash) class C cement+ 4% bwoc Bentonite II+ 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

21-Jun-2016 "

Stage 2

<u>Lead</u>: 600 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Stage 3

<u>Lead</u>: 600 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Matt Dickson Drilling Engineer (432)689-5204 mdickson@legacylp.com