Form 3160-5 (June 2015)

UNITED STATES DEPARTMENT OF THE INTERIOR BUREAU OF LAND MANAGEMENT

FORM APPROVED OMB NO. 1004-0137 Expires: January 31, 2018

BUREAU OF LAND MANAGEMENT				5. Lease Serial No.	
SUNDRY NOTICES AND REPORTS ON WELLS Hobbs Do not use this form for proposals to drill or to re-enter an abandoned well. Use form 3160-3 (APD) for such proposals.				NMNM40406	
				6. If Indian, Allottee or Tribe Name	
SUBMIT IN TRIPLICATE - Other instructions on page 2				7. If Unit or CA/Agreement, Name and/or No.	
1. Type of Well ☐ Gas Well ☐ Other				8. Well Name and No. HAMON FED CO	M A 5H
Name of Operator LEGACY RESERVES OPERA	DICKSON DICKSON DICKSON	JCD	9. API Well No. 30-025-43230		
2. Name of Operator Contact: LEGACY RESERVES OPERATING LÆ-Mail: mdickson@ 3a. Address 303 W WALL ST STE 1800 MIDLAND, TX 79701		FII. 432-009-3200 Ext. 0204		10. Field and Pool or Exploratory Area TEAS; BONE SPRING, EAST	
4. Location of Well (Footage, Sec., T.		WED	11. County or Parish,	State	
Sec 6 T20S R34E SWSE 605FSL 1998FEL		RECEIVED		LEA CO COUNTY, NM	
12. CHECK THE AF	PROPRIATE BOX(ES) TO I	NDICATE NATURE OI	F NOTICE,	REPORT, OR OTH	IER DATA
TYPE OF SUBMISSION	TYPE OF ACTION				
Notice of Intent ■ Notice of Intent	☐ Acidize	□ Deepen	☐ Product	ion (Start/Resume)	■ Water Shut-Off
	☐ Alter Casing	☐ Hydraulic Fracturing	☐ Reclamation		■ Well Integrity
☐ Subsequent Report	Subsequent Report ☐ Casing Repair ☐ New		☐ Recomplete		Other
☐ Final Abandonment Notice	☐ Change Plans	☐ Plug and Abandon	☐ Temporarily Abandon		
	☐ Convert to Injection	☐ Plug Back	☐ Water Disposal		
testing has been completed. Final Abdetermined that the site is ready for final Legacy Reserves Operating reintermediate casing cement putilizing two DV tools. Both DV shoe and a minimum of 200 fee	operations. If the operation results in andonment Notices must be filed only mal inspection. espectfully request approval to rocedures. This option would all tools shall be set a minimum out above the current shoe and owing update to the cementing	add an additional option llow for a three-stage cer of 50 feet below the prev adjust cement proportio	for the ment job rious casing nately base	n, have been completed a	and the operator has
well alread	40140				
14. I hereby certify that the foregoing is	Electronic Submission #37969	ES OPERATING LP, sent	to the Hobb	s /	
Name (Printed/Typed) MATT DIC					
			/		
Signature (Electronic S	Submission)	Date 06/23/20	O17 ACC	EPTED FOR I	RECORD
8	THIS SPACE FOR FI	EDERAL OR STATE	OFFICE U	SE / //	
Approved By		Title		MAR 14 20	18 Hate
Conditions of approval, if any, are attache certify that the applicant holds legal or equ which would entitle the applicant to condu	arrant or	B	REAU OF LAND MAN	XIIII	
Title 18 U.S.C. Section 1001 and Title 43 States any false, fictitious or fraudulent	U.S.C. Section 1212, make it a crime statements or representations as to any	for any person knowingly and matter within its jurisdiction.	willfully to n		

(Instructions on page 2)

** OPERATOR-SUBMITTED ** OPERATOR-SUBMITTED ** OPERATOR-SUBMITTED **

Hamon #5H

Intermediate Casing

In the event that circulation is lost (> 50%) while drilling the 12-1/4" intermediate hole in the Capitan Reef at +/-4000', we will plan to install a DV tool and external casing packer within 200' of the top depth where lost circulation occurred and will pump a two-stage cement job with the potential to add an additional DV tool for a three-stage cement job. If there is no lost circulation a single stage cementing procedure will be followed. Legacy plans to cement to surface regardless of whether a single stage, 2-stage or 3-stage procedure is implemented.

No DV tool (80% excess on lead & 80% excess on tail to design for cement top at surface)

<u>Lead:</u> 1400 sx (35:65) poz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0.25% bwoc FL- 52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

<u>Tail:</u> 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

With (1) DV Tool (100% excess on lead & 100% excess on tail to design for cement top at surface)

Assuming DV tool set at 3950' but if the setting depth changes, cement volumes will be adjusted proportionately.

Stage 1

<u>Lead:</u> 400 sx (35:65) paz (fly ash) class C cement+ 4% bwoc Bentonite II+ 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Stage 2

<u>Lead</u>: 1100 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

With (2) DV Tools (100% excess on lead & 100% excess on tail to design for cement top at surface)

Assuming one DV tool set at 3950' and one DV tool set at 1800' but if the setting depths change, cement volumes will be adjusted proportionately.

Stage 1

<u>Lead:</u> 400 sx (35:65) paz (fly ash) class C cement+ 4% bwoc Bentonite II+ 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk cello flake+ 0.005 lbs/sk defoamer + 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

<u>Tail:</u> 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Stage 2

<u>Lead</u>: 600 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

Tail: 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Stage 3

<u>Lead</u>: 600 sx (35:65) paz (fly ash) class C cement+ 4% bwoc bentonite II + 5% bwoc MPA-5 + 0,25% bwoc FL-52 + 5 lbs/sack LCM-1 + 0.125 lbs/sk Cello Flake+ 0.005 lbs/sk Static Free+ 0.005 gps FP-6L + 1.2% bwoc Sodium Metasilicate + 5% bwow Sodium Chloride (12.5 ppg, 2.13 cfps, 8.81 gps wtr)

<u>Tail:</u> 200 sx class C cement (14.80 ppg, 1.33 cfps, 6.35 gps wtr)

Matt Dickson
Drilling Engineer
(432)689-5204
mdickson@legacylp.com