

Submit 3 Copies  
to Appropriate  
District Office

State of New Mexico  
Energy, Minerals and Natural Resources Department

Form C-103  
Revised 1-1-89

DISTRICT I  
P.O. Box 1980, Hobbs, NM 88240

OIL CONSERVATION DIVISION  
P.O. Box 2088  
Santa Fe, New Mexico 87504-2088

DISTRICT II  
P.O. Drawer DD, Artesia, NM 88210

DISTRICT III  
1000 Rio Brazos Rd., Aztec, NM 87410

WELL API NO. 30-025-31837 ✓
5. Indicate Type of Lease STATE <input checked="" type="checkbox"/> FEE <input type="checkbox"/>
6. State Oil & Gas Lease No. B-1520-1
7. Lease Name or Unit Agreement Name VACUUM GLORIETA WEST UNIT
8. Well No. 11
9. Pool name or Wildcat VACUUM GLORIETA
10. Elevation (Show whether DF, RKB, RT, GR, etc.) GR-3998', KB-4012'

SUNDRY NOTICES AND REPORTS ON WELLS  
(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A  
DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT"  
(FORM C-101) FOR SUCH PROPOSALS.)

1. Type of Well: OIL WELL <input type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER WATER INJECTION
2. Name of Operator TEXACO EXPLORATION AND PRODUCTION INC.
3. Address of Operator P. O. Box 3109 Midland, Texas 79702
4. Well Location Unit Letter <u>B</u> : <u>246</u> Feet From The <u>NORTH</u> Line and <u>1554</u> Feet From The <u>EAST</u> Line Section <u>25</u> Township <u>17-SOUTH</u> Range <u>34-EAST</u> NMPM LEA County

11. Check Appropriate Box to Indicate Nature of Notice, Report, or Other Data

<p>NOTICE OF INTENTION TO:</p> <p>PERFORM REMEDIAL WORK <input type="checkbox"/></p> <p>TEMPORARILY ABANDON <input type="checkbox"/></p> <p>PULL OR ALTER CASING <input type="checkbox"/></p> <p>OTHER: _____ <input type="checkbox"/></p>	<p>SUBSEQUENT REPORT OF:</p> <p>PLUG AND ABANDON <input type="checkbox"/></p> <p>CHANGE PLANS <input type="checkbox"/></p> <p>OTHER: _____ <input type="checkbox"/></p>	<p>REMEDIAL WORK <input type="checkbox"/></p> <p>COMMENCE DRILLING OPNS. <input checked="" type="checkbox"/></p> <p>CASING TEST AND CEMENT JOB <input checked="" type="checkbox"/></p> <p>OTHER: SPUD &amp; SURFACE CASING <input checked="" type="checkbox"/></p>	<p>ALTERING CASING <input type="checkbox"/></p> <p>PLUG AND ABANDONMENT <input type="checkbox"/></p>
--	---	--	--

12. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

1. TMBR-SHARP RIG #3 SPUD 11 inch HOLE @ 5:30pm 03-15-93. DRILLED TO 1600'. TD @ 4:30am 3-16-93.
2. RAN 36 JTS OF 8 5/8, 24#, WC-50, STC CASING SET @ 1600'. RAN 10 CENTRALIZERS.
3. DOWELL CEMENTED WITH 450 SACKS CLASS C w/ 4% GEL, 2% Cacl2 (13.5ppg, 1.74cf/s). F/B 200 SACKS CLASS C w/ 2% Cacl2 (14.8ppg, 1.32cf/s). PLUG DOWN @ 4:15pm 03-16-93. CIRCULATED 125 SACKS.
4. NU BOP & TESTED TO 1500#. TESTED CASING TO 1400# FOR 30 MINUTES FROM 12:15am TO 12:45am 3-17-93.
5. WOC TIME 8 HOURS FROM 4:15pm 03-16-93 TO 12:15am 03-17-93. REQUIREMENTS OF RULE 107, OPTION 2:
  1. VOLUME OF CEMENT SLURRY: LEAD 783 (cu.ft), TAIL 264 (cu.ft).
  2. APPROX. TEMPERATURE OF SLURRY WHEN MIXED: 50° F.
  3. EST. FORMATION TEMPERATURE IN ZONE OF INTEREST: 90° F.
  4. EST. CEMENT STRENGTH AT TIME OF CASING TEST: 950 PSI.
  5. ACTUAL TIME CEMENT IN PLACE PRIOR TO TESTING: 8 HOURS.
6. DRILLING 7 7/8 HOLE.

I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNATURE C. P. Basham / cwh TITLE DRILLING OPERATIONS MANAGER DATE 03-17-93

TYPE OR PRINT NAME C. P. BASHAM TELEPHONE NO. 915-6884620

(This space for State Use)

APPROVED BY \_\_\_\_\_ TITLE \_\_\_\_\_ DATE \_\_\_\_\_

CONDITIONS OF APPROVAL, IF ANY:

MAR 22 1993



# CEMENTING REPORT

Job No: H093099 Report Date: 3/10/93  
 Operator: Texaco Requested By: OP  
 Case No: Vac 82, II Service Point: HNM  
 Location: Lea NM Type of Job: Surface

Test Conditions:  
 Depth: 1350 ft., Temp Grad \_\_\_\_\_, BHST: 90 °F, BHCT: 85

Properties:	Density (ppg)	Yield (cu ft/sk)	Mix Water (gal/sk)	Total Liquid (gal/sk)	Water Source	Cement Source
System No. 1	<u>13.5</u>	<u>1.74</u>	<u>9.11</u>	<u>9.11</u>	<u>Loc</u>	<u>C</u>
System No. 2	<u>14.8</u>	<u>1.32</u>	<u>6.32</u>	<u>6.32</u>	<u>Loc</u>	<u>C</u>
System No. 3						
System No. 4						

Cement System Compositions:  
 System No. 1 C + 4% D20 + 2% S1  
 System No. 2 C + 2% S1  
 System No. 3 \_\_\_\_\_  
 System No. 4 \_\_\_\_\_

SYSTEM	HR:MIN	BC	Rheology Results							REHOLOGY MODEL	I.O.I.	
			300	200	100	60	30	6	3			
No. 1	<u>4:10</u>	<u>70</u>	<u>30</u>	<u>24</u>	<u>21</u>	<u>18</u>	<u>15</u>	<u>12</u>	<u>10</u>			
No. 2	<u>2:10</u>	<u>70</u>	<u>45</u>	<u>40</u>	<u>34</u>	<u>30</u>	<u>28</u>	<u>20</u>	<u>15</u>			
No. 3												
No. 4												

Compressive Strengths - psi

SYSTEM	TEMP.	6 HRS.	12 HRS.	HRS.
No. 1	<u>90 °F</u>	<u>490</u>	<u>975</u>	
No. 1	<u>°F</u>			
No. 2	<u>90 °F</u>	<u>575</u>	<u>1700</u>	
No. 2	<u>°F</u>			
No. 3	<u>°F</u>			
No. 3	<u>°F</u>			
No. 4	<u>°F</u>			
No. 4	<u>°F</u>			

SYSTEM	FLUID LOSS		FREE WATER
	°F	psi	ml
No. 1			
No. 2			
No. 3			
No. 4			

Remarks: \_\_\_\_\_  
 \_\_\_\_\_  
 \_\_\_\_\_