

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr. Corp.</i>		Lease <i>Lush Hills yaso / E State</i>		Well # <i>5</i>	
Location of Well	Unit <i>2310N 1650E</i>	Section <i>12</i>	Township <i>19</i>	Range <i>24</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cactus Drilling</i>		Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>15"</i>	<i>10 3/4</i>	<i>32.75</i>		<i>400</i>	<i>275 lin</i>
<i>9 5/8"</i>	<i>7"</i>	<i>20</i>		<i>925</i>	<i>500 "</i>
<i>6 1/4"</i>	<i>4 1/2"</i>	<i>9.5</i>		<i>3000</i>	<i>200 lin.</i>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole *9 1/2"* Size of Casing *7"* Sacks cement required *850*

Type of Shoe used *Guide* Float collar used *Float* Btm 3 jts welded *yes*

TD of hole *925* Set *927* Feet of *7* Inch *20* # Grade *K-55*

New used csg. @ *925* with *150* sacks neat cement around shoe *Cl. C w/ 2% CaCl.*
+ *450* sax *65/35 POZ.* additives *8 lbs/sk Kolite, 4 lbs/sk Coplake, 4% Gel, 3% CaCl*

Plug down @ *1:00* (AM) (PM) PM Date *5-18-80*

Cement circulated *NO* No. of Sacks _____

Cemented by _____ Witnessed by _____

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *+ an additional 250 sacks cl. C w/ 3% CaCl.*

basket @ 400'
SSC 370'
lost circ. 427'
last drilling bk. - 756'