State of New Mexico Form C-103 Submit 3 Copies y, Minerals and Natural Resources Departmer Revised 1-1-89 to Appropriate District Office OIL CONSERVATION DIVISION DISTRICTI WELL API NO. P.O. Box 1980, Hobbs, NM 88240 P.O. Box 2088 30-015-27843 Santa Fe, New Mexico 87504-2088 DISTRICT II 5. Indicate Type of Lease P.O. Drawer DD, Artesia, NM 88210 FEE X STATE MAR 1 5 1994 6. State Oil & Gas Lease No. 1000 Rio Brazos Rd., Aztec, NM 87410 SUNDRY NOTICES AND REPORTS ON WELLS (DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A 7. Lease Name or Unit Agreement Name DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT" (FORM C-101) FOR SUCH PROPOSALS.) Roy AET Type of Well: WEIL X OTHER 8. Well No. 2. Name of Operator YATES PETROLEUM CORPORATION 9. Pool name or Wildcat 3. Address of Operator North Dagger Draw U/Penn (505) 748-1471 88210 105 South 4th St., Artesia, NM 4. Well Location East Feet From The South 660 Line Line and Feet From The Unit Letter . Township 19S 25E **NMPM** Range Section 10. Elevation (Show whether DF, RKB, RT, GR, etc.) 3533' GR Check Appropriate Box to Indicate Nature of Notice, Report, or Other Data SUBSEQUENT REPORT OF: NOTICE OF INTENTION TO: ALTERING CASING PLUG AND ABANDON REMEDIAL WORK PERFORM REMEDIAL WORK PLUG AND ABANDONMENT COMMENCE DRILLING OPNS. **CHANGE PLANS** TEMPORARILY ABANDON CASING TEST AND CEMENT JOB PULL OR ALTER CASING OTHER: Set production casing OTHER: 12. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103. TD 8210'. Reached TD 3-9-94. Ran 200 joints (8820') 7" 26# and 23# J-55 and N-80 casing set 8210'. Float shoe set 8210', float collar set 8169'. DV tool set 5583'. Cemented in two stages. Stage I: 600 sx "H", 5#/sx CSE, ,65% CF-14, 5#/sx Gilsonite, 1/4#/sx Celloseal (yield 1.31, wt 15.1). PD 12:30 AM 3-11-94. Bumped plug to 1500 psi for 1 minute. Circulated 75 sacks cement. Circulated through DV tool 4 hours. Stage 2: 700 sx PSL "C", 5#/sx Salt, 5#/sxGilsonite, .4% CF-14, 1/4#/sx Celloseal (yield 1.99, wt 12.5). Tailed in with 100 sx Class "H" Neat, (yield 1.18, wt 15.6). PD 6:30 AM 3-11-94. Bumped plug to 2000 psi for 1 minute, held OK. Circulated 56 sacks cement. WOC 18 hours.

TYPE OR PRINT NAME

Juanita Goodlett

This space for State Use)

Production Supervisor

THE PRODUCTION NO. 505/748-1471

SUPERVISOR DISTRICT IL

円角質 3 (1994 - Date -----

CONDITIONS OF APPROVAL, IF ANY: