

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Amoco Prod Co</u>		Lease <u>State IN</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980^W 1980^E G</u>	Section <u>1</u>	Township <u>24</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor			Type of Equipment <u>Rotary</u>		
* Witness					
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8</u>	<u>48[#]</u>		<u>400'</u>	<u>Sur</u>
* <u>12 1/4</u>	<u>9 5/8</u>	<u>36[#]</u>		<u>2600'</u>	<u>Sur</u>
<u>3 3/4</u>	<u>5 1/2</u>	<u>17[#] - 20[#] - 23[#]</u>		<u>10,850</u>	
Casing Data:					
Surface <u>68</u> joints of <u>9 5/8"</u> inch <u>36</u> # Grade <u>K-55</u>					
(Approved) (Rejected)					
Inspected by <u>Larry Brooks</u> date <u>7-12-80</u>					
Cementing Program					
Size of hole <u>12 1/4"</u> Size of Casing <u>9 5/8"</u> Sacks cement required <u>1550 SXS</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>diff. fill collar</u> Btm 3 jts welded <u>Yes.</u>					
TD of hole <u>2700'</u> Set <u>2681.4</u> Feet of <u>9 5/8</u> Inch <u>36</u> # Grade <u>K-55</u>					
(New) used csg. @ <u>2681.4</u> with <u>250</u> sacks * neat cement around shoe * Cl. C w/2% CaCl.					
+ <u>1300</u> sax <u>HALLIBURTON LITE</u> additives <u>10 lbs/sk. Gilsomite, 1/4" sx. floccule.</u>					
Plug down @ <u>8:40</u> (AM) (PM) Date <u>7-12-80</u>					
Cement circulated <u>YES</u> No. of Sacks <u>190 SXS.</u>					
Cemented by <u>HALLIBURTON (DEWEY GREENE)</u> Witnessed by <u>LARRY BROOKS.</u>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks:					

Lost circ. @ - NO LOSS

Cent. @ - SHOE - 2681.4 - FLOAT - 2639.4
Baskets @ - NONE