

PAGE START DATE: 2/21/97
PAGE START TIME: 19:44:00
DATA FILE: 11

DELTA TIME HRS	DEPTH FEET	TEMPERATURE 'F	COMMENTS
0.000	30.00	60.00	
0.250	320.00	67.00	BREAK
0.300	388.00	76.75	
0.317	412.00	77.50	
0.333	436.00	86.75	
0.350	460.00	95.50	
0.383	509.00	97.75	
0.400	535.00	98.50	
0.417	565.00	103.50	
0.433	596.00	100.25	
0.450	610.00	119.50	M.D.R.

DATE AND TIME CEMENT JOB COMPLETE:

FEBRUARY 21, 1997 @ 1:30 PM

DATE AND TIME SURVEY MADE:

FEBRUARY 21, 1997 @ 7:30 PM

AMOUNT AND TYPE CEMENT USED:

300 SACKS HALIBURTON LIGHT PREMIUM WITH
6% GEL AND 2% CALCIUM CHLORIDE FOLLOWED BY
250 SACKS PREMIUM PLUS CLASS C WITH 2%
CALCIUM CHLORIDE AND 1/4# FLOSEAL, RUN
BEHIND 675 FEET OF 13-3/8" CASING IN A
17 1/2" HOLE.

DEPTH FIGURED FROM:

KELLY BUSHING