Form 3160-5 (June 1990)

## **UNITED STATES** \* DEFARTMENT OF THE INTERIOR **BUREAU OF LAND MANAGEMENT**

FORM APPROVED		
Budget Bureau No. 1004-0135		
Expires:	March 31, 1993	

Budget Bur	eau No. 1004-0.	135
Expires:	March 31, 1993	3

5. Lease	Designation	and	Serial	No.
M01364				

SUNDRY NOTICES AND REPORTS ON WELLS	•		
Do not use this form for proposals to drill or to deepen or reentry to a different	t re	servo	ir.
Use "APPLICATION FOR PERMIT—" for such proposals	13	1	23

6. If Indian, Allottee or Tribe Name

Use "APPLICATION FOR PE	RMIT—" for such proposals 703 Jul 23	MNA 07
SUBMIT IN T	<b>RIPLICATE</b> 070 Farmin	Old MA
1. Type of Well Oil Well X Gas Well Other	A CONTROL OF THE PARTY OF THE P	8. Well Name and No.
2. Name of Operator  Koch Exploration Company, LLC	R 01 2003 72 32 4	Federal Blancett Com C1A  9. API Well No. 3004531389
3. Address and Telephone No. P.O. Box 489 Aztec, NM 87410	(505) 334-9111	10. Field and Pool, or Exploratory Area Basin Fruitland Coal
4. Location of Well (Footage, Sec., T., R., M., or Survey De S27, T32N, R9W (I) 1745 FSL & 1170 FEL	sscription)	11. County or Parish, State  San Juan County  New Mexico
12. CHECK APPROPRIATE BOX(s) TO	O INDICATE NATURE OF NOTICE	, REPORT, OR OTHER DATA
TYPE OF SUBMISSION	TYPE OF	ACTION
Notice of Intent	Abandonment Recompletion	Change of Plans  New Construction
X Subsequent Report	Plugging Back  Casing Repair	Non-Routine Fracturing  Water Shut-Off
Final Abandonment Notice	Altering Casing    X Other Surface Casing Cement	Conversion to Injection  Dispose Water  Note: Report results of multiple completion on Well Completion or Recompletion Report and Log form.)
Describe Proposed or Compelted Operations (Clearly state all pertigive subsurface locations and measured and true vertical depth	inent details, and give pertinent dates, including estimated date of s	

Drilled 12 1/4" hole and ran 9 5/8", J-55, 36#, ST&C casing and landed at 232' KB. KB = 13'0"

Ran centralizers on the bottom 3 joints including shoe joint. Cemented with 120 sks 15.8# Class G Cement with 2% CaCl2, .25 lb/sk D29 Cellofane, yield 1.16. Had good cement returns to surface. WOC 12 hours.

7/15/03 - Pressure tested casing to 700 psi for 30 min. Held OK.

I hereby estrict that the foregoing is true and charact	Title District Superintendent	Data CCEDITATO PERO DECORA
(This space 14 Federal or State office use)	2 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3	ACCEPTED FOR RECORD
Approved by Date	Title	
Conditions of approval, if any:		002 2 9 (00)
		CROSSING ALLE IN APPIAR