

30-039-06939

DATE: 4-12-96DATA SHEET FOR DEEP GROUND BED CATHODIC PROTECTION WELLS
NORTHWESTERN NEW MEXICOOperator Meridian Oil Location: Unit A Sec. 26 Twp 27 Rng 4Name of Well/Wells or Pipeline Serviced San Juan 27-4 #29Elevation _____ Completion Date 4-12-96 Total Depth _____ Land Type FCasing Strings, Sizes, Types & Depths 60' of 8" PVC CasingIf Casing Strings are cemented, show amounts & types used Yes - 17 sacksIf Cement or Bentonite Plugs have been placed, show depths & amounts used
NoneDepths & thickness of water zones with description of water: Fresh, Clear,
Salty, Sulphur, Etc. 100' Fresh**RECEIVED**
FEB 19 1997Depths gas encountered: 200' OIL CON. DIV.Ground bed depth with type & amount of coke breeze used: 384'
5500 lbs Asbury Coke BreezeDepths anodes placed: 315', 250', 215', 209', 194', 188', 182', 176', 170', 164', 158', 145', 135', 125', 118'Depths vent pipes placed: Surface to 384'Vent pipe perforations: From 109' to 384'Remarks: Driller smelled a little gas at 200-210'. This well has recently been sidetracked

If any of the above data is unavailable, please indicate so. Copies of all logs, including Drillers Log, Water Analyses & Well Bore Schematics should be submitted when available. Unplugged abandoned wells are to be included.

Land Type may be shown: F-Federal; I-Indian; S-State; P-Fee.
If Federal or Indian, add Lease Number.

CPS GROUND BED CONSTRUCTION WORKSHEET

CPS#	2959-4					P/L NAME(S), NUMBER(S)	San Juan 27-4 #29		
WO #	ZE 97	TOTAL	VOLTS	AMPS	- OHMS	DATE	NAME		
			12.4	21.4	.56	4-12-96	David Ashworth		
REMARKS (notes for construction log)									
PerF 275' 384-TD Drilled 400 17 Sacks Cement									
H2O-100' 5500 lbs Ash Gas at 200'									

DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	
	ANODE	*		ANODE	*		ANODE	*		ANODE	*	
100			295	.3		490			685			
105			300	.3		495			690			
110			305	.3		500			695			
115	2.2		310	.6		505			700			
120	2.5		315	1.5		510			ANODE	DEPTH	NO	FULLY
125	2.5		320	.9		515			*	COKE	COKE	COKE
130	3.2		325	.6		520			1	315	1.5	3.0
135	3.2		330	.6		525			2	250	1.6	3.4
140	1.6		335	.6		530			3	215	2.1	5.4
145	1.4		340	.6		535			4	209	1.4	5.4
150	1.1		345	.6		540			5	194	1.9	7.1
155	1.1		350	.7		545			6	189	2.4	8.2
160	1.9		355	.8		550			7	182	2.4	8.6
165	2.3		360	.9		555			8	176	3.0	9.1
170	3.3		365	.6		560			9	170	3.0	8.9
175	2.9		370	.6		565			10	164	2.0	7.7
180	2.4		375	.8		570			11	158	1.1	4.5
185	2.4		380	.8		575			12	145	1.4	5.0
190	2.0		385	.8		580			13	135	2.2	8.5
195	1.3		390	384-TD		585			14	125	2.5	7.8
200	1.0		395			590			15	118	2.2	7.7
205	.9		400			595			16			
210	2.2		405			600			17			
215	1.5		410			605			18			
220	.5		415			610			19			
225	.2		420			615			20			
230	.2		425			620			21			
235	.2		430			625			22			
240	.2		435			630			23			
245	.7		440			635			24			
250	1.6		445			640			25			
255	1.3		450			645			26			
260	.6		455			650			27			
265	.2		460			655			28			
270	.2		465			660			29			
275	.2		470			665			30			
280	.2		475			670						
285	.3		480			675						
290	.3		485			680						

DISTRIBUTION - original - permanent CPS FILE

copy - Division Corrosion Supervisor
copy - Region Corrosion Specialist