

635

30-045-27759

E

2259W

DATA SHEET FOR DEEP GROUND BED CATHODIC PROTECTION WELLS
NORTHWESTERN NEW MEXICOOperator Meridian Location: Unit M Sec. 16 Twp 32 Rng 9Name of Well/Wells or Pipeline Serviced SAN JUAN 32.9 #217Elevation 6890 Completion Date 7.19.91 Total Depth 380 Land Type FCasing Strings, Sizes, Types & Depths 100" PVC 8"If Casing Strings are cemented, show amounts & types used 20 BAGSNEAT CEMENT

If Cement or Bentonite Plugs have been placed, show depths & amounts used

NO

Depths & thickness of water zones with description of water: Fresh, Clear,

Salty, Sulphur, Etc. 130', 150' DAMP ONLYDepths gas encountered: NOGround bed depth with type & amount of coke breeze used: 380'with 54 BAGS of Asbury 4518 FLO COKEDepths anodes placed: 360, 350, 340, 330, 320, 310, 300, 285, 275, 230, 220, 20Depths vent pipes placed: 380'Vent pipe perforations: FROM 80' TO 380'

RECEIVED

FEB 24 1992

Remarks:

OIL CON. DIV.
DIST. 3

If any of the above data is unavailable, please indicate so. Copies of all logs, including Drillers Log, Water Analyses & Well Bore Schematics should be submitted when available. Unplugged abandoned wells are to be included.

Land Type may be shown: F-Federal; I-Indian; S-State; P-Fee.

If Federal or Indian, add Lease Number.

CPS GROUND BED CONSTRUCTION WORKSHEET

CPS#	P/L NAME(s), NUMBER(s)					
2259-W	SAW JUAN 32-9 #217					
* 2801	TOTAL	VOLTS	AMPS	-- OHMS	DATE	NAME
		11.08	23.1	48	7-19-91	MRW
REMARKS (notes for construction log)						
100' 8" PVC SURFACE CASING ; 20 SACKS CEMENT --						
DAMP AT 130' < 150' blew ^{WATER} sample AT 150' NOT ENOUGH FOR SAMPLE						
54 BAGS COKE Elev. 6840' A 16-32-9 Drilled 380 LOGGED						

DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	DEPTH	LOG	ANODE	
	ANODE	*		ANODE	*		ANODE	*		ANODE	*	
100			295	3.0		490			685			
105			300	3.0	7	495			690			
110			305	3.0		500			695			
115			310	3.5	6	505			700			
120			315	3.3		510			ANODE	DEPTH	NO.	FULLY
125			320	3.5	5	515			*		COKE	COKE D
130			325	3.5		520			1	360	3.6	6.9
135			330	3.3	4	525			2	350	3.1	6.6
140			335	2.9		530			3	340	3.2	6.6
145			340	3.2	3	535			4	330	3.5	6.7
150	.9		345	3.3		540			5	320	3.4	6.9
155	.9		350	3.2	2	545			6	310	3.5	6.9
160	1.0		355	3.0		550			7	300	3.1	6.3
165	1.5		360	3.6	1	555			8	285	3.3	6.4
170	2.7		365	3.0		560			9	275	3.4	6.1
175	4.0		370	2.8		565			10	230	3.5	6.0
180	4.0		375	2.6		570			11	220	3.9	7.0
185	3.0		380	2.1		575			12	210		
190	3.4		385			580			13	205	4.1	6.9
195	3.1		390			585			14			
200	3.5		395			590			15			
205	4.0		400			595			16			
210	3.7	12	405			600			17			
215	3.9		410			605			18			
220	3.8	11	415			610			19			
225	3.8		420			615			20			
230	3.1	10	425			620			21			
235	1.7		430			625			22			
240	1.2		435			630			23			
245	1.0		440			635			24			
250	1.0		445			640			25			
255	1.0		450			645			26			
260	1.1		455			650			27			
265	1.9		460			655			28			
270	2.8		465			660			29			
275	3.5	9	470			665			30			
280	3.5		475			670						
285	3.0	8	480			675						
290	2.5		485			680						

DISTRIBUTION - original - permanent CPS FILE

copy - Division Corrosion Supervisor

copy - Region Corrosion Specialist