Form 3160-5 November 19 3) Formerty 9-3 1)	DEPARTM	JNITED STATES IENT OF THE INTERI J OF LAND MANAGEMENT		5. LEASE DESIGNATION SF-078359	31, 1985 and Berial no.	
(Do not		CES AND REPORTS Calls to drill or to deepen or plug by	ack to a different reservoir.	6. IF INDIAN, ALLOTTEE  Navajo Fee	OR TRIBE NAMI	
1.				7. UNIT AGREEMENT NAM	ME	
WELL X GAS				8. FARM OR LEASE NAM		
Bannon Energy, Inc.					Marcus A	
3. ADDRESS OF OPERA				9. WELL NO.		
P.O. Box 2058 Farmington NM 87499				4	.}	
4. LOCATION OF WELL See also space 17	10. FIELD AND POOL, OR WILDCAT					
At surface 965 FNL X				Counselors 11. SEC., T., E., M., OR B. SURVEY OR AREA	Gallup LE. AND	
		Life Street world Chart whether Dr	P. C.P. oto.)	Sec. 18 T2		
14. PERMIT NO.		15. ELEVATIONS (Show whether DF	, n.i., GR, Coo.)	i	NM	
		6869 GR		Rio Arriba	I INE'I	
6.	Check Ap	propriate Box To Indicate N	lature of Notice, Report, or	r Other Data		
	NOTICE OF INTENTION TO:			UENT REPORT OF:		
TEST WATER SHU	T-OFF	PULL OR ALTER CASING	WATER SHUT-OFF	BEPAIRING W	TELL	
FRACTURE TREAT		HULTIPLE COMPLETE	FRACTUBE TREATMENT	ALTERING CA		
SHOOT OR ACIDIZE	G	ABANDON*	SHOOTING OR ACIDIZING	ABANDONMEN	T*	
REPAIR WELL (Other)	<u> </u>	THANGE PLANS	(Other) Completion  (Note: Report results of multiple completion on Well Completion or Recompletion Report and Log form.)			
	PARAMETER OF THE PARAME	AUG ONL				
APPROVED BY	Federal or State off	ce use)	erating Agent	ACCEPPED® FOR R	ECORD	
		*See Instruction	D 0:1	FARMINGTON RESOURCE	E AREA	

Title 18 U.S.C. Section 1991, makes it a crime for any person knowingly and willfully to make to any department or agency of the

## Casing and Cement Summary

TD- 5650 Ran 136 joints, 4 1/2", 11.6 lb., K-55 casing.

Measured , set at 5650 Float collar- (KB)

Stage collar- 2987 (KB). First stage cemented as follows:

Pump 10 bbls. fresh water, 10 bbls. CaCl<sup>2</sup> water, 10 bbls. fresh water, 12 bbls. Flocheck-21, 10 bbls. water spacer followed by 315 sacks, (595 cu. ft.) 65-35 pozmix, 2% gel, 6 1/4 lbs. Gilsonite and 6 lbs. salt per sack. Followed w/100 sks (170 cu ft.) 50-50 poz + 2% gel Circulated cement by stage collar. Circulated 4 hours between stages.

Second stage - same spacer program as the first stage followed by 450 sacks, (850 cu. ft.) 65-35 pozmix, 6% gel, 3 lbs. Hi Seal per sack followed by 50 sacks, (60 cu. ft.) Class "B" cement. Plug down

