

Cement Record

8 5/8" Casing →

575 syx Class 8" near cement w/29% CaCl₂

CT $\rightarrow$ Surface

4 1/2" Casing → 1st

420 SX Class "B" meat cement w/ 50:50 pot, 6% gal, 2nd med tut plug/sx, .8% fluid

loss additive. 100 SK Class "B" neat cement.

2nd 1100 SX Class "B" near center w/ 65:35 pos,

6% gel, 2nd med w/ plug/sx, .8% fluid

loss additive, 100 sX class "B" near cement

$CT \rightarrow 500'$

