

(SUBMIT IN TRIPLICATE)


Land Office Santa FeLease No. NM 03357Unit Northeast Blanco

UNITED STATES  
DEPARTMENT OF THE INTERIOR  
GEOLOGICAL SURVEY Unit Agrmt. No. 1, Sec. 929

## SUNDRY NOTICES AND REPORTS ON WELLS

NOTICE OF INTENTION TO DRILL	SUBSEQUENT REPORT OF WATER SHUT-OFF	<input checked="" type="checkbox"/>
NOTICE OF INTENTION TO CHANGE PLANS	SUBSEQUENT REPORT OF SHOOTING OR ACIDIZING	
NOTICE OF INTENTION TO TEST WATER SHUT-OFF	SUBSEQUENT REPORT OF ALTERING CASING	
NOTICE OF INTENTION TO RE-DRILL OR REPAIR WELL	SUBSEQUENT REPORT OF RE-DRILLING OR REPAIR	
NOTICE OF INTENTION TO SHOOT OR ACIDIZE	SUBSEQUENT REPORT OF ABANDONMENT	
NOTICE OF INTENTION TO PULL OR ALTER CASING	SUPPLEMENTARY WELL HISTORY	
NOTICE OF INTENTION TO ABANDON WELL		

(INDICATE ABOVE BY CHECK MARK NATURE OF REPORT, NOTICE, OR OTHER DATA)



July 14, 1961

Well No. 62-30 is located 1470 ft. from NW line and 1250 ft. from EX line of sec. 30SW/4 Sec. 30  
(1/4 Sec. and 1/4 Sec. No.)31N  
(Twp.)6W  
(Range)NMPM  
(Meridian)Blanco Mesaverde  
(Field)Rio Arriba  
(County or Subdivision)New Mexico  
(State or Territory)The elevation of the derrick floor above sea level is 6374 ft.

Spudded at 7:00 PM 6-24-61

## DETAILS OF WORK

(State names of and expected depths to objective sands; show sizes, weights, and lengths of proposed casings; indicate mudding jobs, cementing points, and all other important proposed work)

On 6/25/61, ran 6 Jts 10 1/2" 32.75# H40 casing - 192' set at 208'. Cemented with 225 sacks regular cement with 2% HA-5 added. Cement circulated. Tested casing with 800 PSI for 15 minutes. Held OK.

On 7/1/61, ran 8 1/2 Jts 7-5/8" 26.40# J55 casing - 3435' set at 3450'. Cemented with 350 sacks 1:1 cement and Pozmix S with 4% gel and 12 1/2# Gilsomite per sack. Top of cement at 1175' by temperature survey. Tested casing with 1000 PSI for 30 minutes. Held OK. Drilled with gas from 7-5/8" casing point.

On 7/4/61, ran 179 Jts 5 1/2" 15.50# J55 casing - 5795' set at 5809'. Cemented with 100 sacks 1:1 cement and Pozmix S with 4% gel and 12 1/2# Gilsomite per sack, followed with 75 sacks regular cement with 1 lb. Halad-9 per sack. Top of cement at 4740' by temperature survey. Tested casing with 1500 PSI for 15 minutes. Held OK.

I understand that this plan of work must receive approval in writing by the Geological Survey before operations may be commenced.

Company Blackwood & Nichols CompanyAddress P.O. Box 1237Durango, ColoradoBy Delasso LoosTitle Field Superintendent