

NO. OF COPIES RECEIVED	3
DISTRIBUTION	
SANTA FE	1
FILE	1
U.S.G.S.	
LAND OFFICE	
OPERATOR	1

NEW MEXICO OIL CONSERVATION COMMISSION

Form C-103
Supersedes Old
C-102 and C-103
Effective 1-1-65

5a. Indicate Type of Lease	State <input checked="" type="checkbox"/> Fee <input type="checkbox"/>
5. State Oil & Gas Lease No.	E-505-6

SUNDRY NOTICES AND REPORTS ON WELLS

(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT -" (FORM C-101) FOR SUCH PROPOSALS.)

1. OIL WELL <input type="checkbox"/> GAS WELL <input checked="" type="checkbox"/> OTHER- <input type="checkbox"/>	7. Unit Agreement Name Northeast Blanco Unit
2. Name of Operator Blackwood & Nichols Co., Ltd.	8. Farm or Lease Name Northeast Blanco Unit
3. Address of Operator P. O. Box 1237, Durango, Colorado 81301	9. Well No. 22A
4. Location of Well UNIT LETTER O, 910 FEET FROM THE S LINE AND 1970 FEET FROM THE E LINE, SECTION 36 TOWNSHIP 31N RANGE 7W NMPM.	10. Field and Pool, or Wildcat Blanco Mesaverde
15. Elevation (Show whether DF, RT, GR, etc.) 6458' GL	12. County Rio Arriba

16.

Check Appropriate Box To Indicate Nature of Notice, Report or Other Data

NOTICE OF INTENTION TO:

PERFORM REMEDIAL WORK ☐
TEMPORARILY ABANDON ☐
PULL OR ALTER CASING ☐
OTHER ☐

PLUG AND ABANDON ☐
CHANGE PLANS ☐
OTHER ☐

SUBSEQUENT REPORT OF:

REMEDIAL WORK ☐
COMMENCE DRILLING OPNS. ☐
CASING TEST AND CEMENT JOB ☒
OTHER ☐

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

On September 27, 1977, set 212' of 9-5/8", 36.00#, H-40 casing at 227'-13-3/8" hole. Cemented with 225 sacks of Class B cement with 2% CaCl₂; Cement circulated. On 9-28-77, tested 9-5/8" casing with 800 PSI for thirty minutes. Held OK.

On October 4, 1977, set 3632' of 7", 23.00#, K-55 casing at 3647' - 8-3/4" hole. Cemented with 200 sacks of Howco light cement with 1/4# flocele/sk; followed with 100 sacks of Class B with 2% CaCl₂ and 1/4# flocele/sack. Ran temperature survey; top cement 1600'. Tested 7" casing with 1000 PSI for thirty minutes, held OK.

On October 7, 1977, set 5903', 4-1/2" - 10.50# K-55 set at 5914'; cemented with 200 sacks of Class C cement with 4% gel and .6% CFR-2 and 1/4# flocele per sack; followed with 100 sacks of Class B cement with .6% CFR-2 and 1/4# flocele/sack. Ran Temperature survey; top of cement 3525'.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED A. R. Kendrick TITLE District Manager DATE 10-12-77

Original Signed by A. R. Kendrick

APPROVED BY _____ TITLE _____ DATE _____

CONDITIONS OF APPROVAL, IF ANY: