

NO. OF COPIES RECEIVED		
DISTRIBUTION		
CANTAFE		
FILE		
U.S.G.S.		
LAND OFFICE		
OPERATOR		

# NEW MEXICO OIL CONSERVATION COMMISSION

Form C-103  
Supersedes Old  
C-102 and C-101  
Effective 1-1-65

5a. Indicate Type of Lease	
State <input type="checkbox"/>	Fee <input checked="" type="checkbox"/>
5. State Oil & Gas Lease No.	
7. Unit Agreement Name	
8. Farm or Lease Name	
Amistad Land & Cattle Co.	
9. Well No.	
1	
10. Field and Pool, or Wildcat	
Wildcat	
12. County	
Union	

## SUNDRY NOTICES AND REPORTS ON WELLS

(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT - I" (FORM C-101) FOR SUCH PROPOSALS.)

OIL WELL <input type="checkbox"/>	GAS WELL <input type="checkbox"/>	OTHER - Carbon Dioxide
Name of Operator		
CO2 In Action, Inc.		
Address of Operator		
P. O. Box 2748 Amarillo, Texas 79105		
Location of Well		
UNIT LETTER E	330	FEET FROM THE West
LINE AND	2310	FEET FROM
THE North	18	TOWNSHIP 19 N
RANGE	36 E	NMPM.

15. Elevation (Show whether DF, RT, GR, etc.)
K.B. 4479

Check Appropriate Box To Indicate Nature of Notice, Report or Other Data

NOTICE OF INTENTION TO: SUBSEQUENT REPORT OF:

PERFORM REMEDIAL WORK <input type="checkbox"/>	PLUG AND ABANDON <input type="checkbox"/>	REMEDIAL WORK <input type="checkbox"/>	ALTERING CASING <input type="checkbox"/>
TEMPORARILY ABANDON <input type="checkbox"/>	CHANGE PLANS <input type="checkbox"/>	COMMENCE DRILLING OPNS. <input type="checkbox"/>	PLUG AND ABANDONMENT <input type="checkbox"/>
PULL OR ALTER CASING <input type="checkbox"/>	OTHER <input type="checkbox"/>	CASING TEST AND CEMENT JOBS <input checked="" type="checkbox"/>	

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

On May 9, 1981 we ran 5-1/2" casing to 3610'. We ran:  
78 joints, 5-1/2" casing, 14#, K-55, ST&C, 3428'.  
We cemented with 950 sacks class H, 2% cc, 2% gel, 5% KCL, 5#  
gilsonite per sack, 1/4# celloseal per sack, 4% CF9 mixed at  
14.4# with a yield of 1.5 ft3 per sack. We circulated 100 sacks  
of cement and subsequent bond log shows the top of cement to be 114'.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED Ernest J. Haden TITLE Geologist DATE March 10, 1982

APPROVED BY Carl H. Hagen TITLE  DATE 3-15-82

CONDITIONS OF APPROVAL, IF ANY: