

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Petrol Corporation</u>		Lease <u>Cecil Johnson</u>		Well # <u>1</u>	
Location of Well	Unit <u>6605-1980W</u>	Section <u>8</u>	Township <u>12</u>	Range <u>26</u>	County <u>Chaves</u>
Drilling Contractor <u>Leonard George</u>			Type of Equipment <u>Rotary & start 9-24-76</u>		

APPROVED CASING PROGRAM

* witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>12 3/4" 15"</u>	<u>48</u>	<u>used</u>	<u>75</u>	<u>Circ.</u>
<u>11"</u>	<u>8 5/8"</u>	<u>28</u>	<u>used</u>	<u>1100</u>	<u>Circ.</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>10.5</u>	<u>used</u>	<u>1500</u>	<u>150</u>

Casing Data:

Surface 26 joints of 8 3/8 inch 28 # Grade API New H-40
(Approved) (Rejected)

Inspected by John Mermin date 10-17-76

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8 Sacks cement required 550/SK

Type of Shoe used Texas Float collar used Insert Btm 2 jts ~~welded~~ Thread Lock

TD of hole 1033' KD Set 1029' Feet of 8 5/8 Inch 28 # Grade H-40

New-used csg. @ 1029' GL with 200/SK sacks neat cement around shoe class 2%cc
+ 350 sax Newco Lite additives 5# Gilsomite 1/4" Hecole 2%cc

Plug down @ 3:00 (~~AM~~) (PM) Date 10-17-76

Cement circulated Yes No. of Sacks 120/SK

Cemented by Halliburton Witnessed by John Mermin

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: