

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 100
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Supron Energy Corp.</u>		Lease <u>Amoco State</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980542</u>	Section <u>16</u>	Township <u>17</u>	Range <u>26</u>	County <u>Chaves</u>
Drilling Contractor	<u>and Drilg. Co.</u>		Type of Equipment <u>Rotary to start 5-22-78</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>300</u>	<u>315 line.</u>
<u>12 1/4"</u>	<u>8 3/8"</u>	<u>24</u>		<u>1500</u>	<u>750 "</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.6</u>		<u>6200</u>	<u>300</u>
Casing Data:					
Inter. <u>Surface</u> joints of <u>8 5/8</u> inch <u>24</u> # Grade <u>K-55</u>					
(Approved) (Rejected)					
Inspected by <u>M. S.</u> date <u>6/5/78</u>					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>875</u>					
Type of Shoe used <u>guide</u> Float collar used <u>insert</u> Btm 2 jts welded <u>yes</u>					
TD of hole <u>1360'</u> Set <u>1360'</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>K-55</u>					
New-used csg. @ <u>1360'</u> with <u>200</u> sacks neat cement around shoe					
+ <u>675</u> sax <u>50/50 per.</u> additives <u>4% Bentonite, 2% occ 1/4 lb collo, 5 lb salt.</u>					
Plug down @ <u>12:00</u> (AM) (PM) Date <u>6/6/78</u>					
Cement circulated <u>No</u> No. of Sacks					
Cemented by <u>Dowell</u> Witnessed by <u>Mike Stubbfield</u>					
Temp. Survey ran @ <u>6:00</u> (AM) (PM) Date <u>6/7/78</u> top cement @ <u>530'</u>					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <u>3 centralizers @ 10' above shoe, 2nd collar, 3rd collar.</u>					
<u>Well never lost circ. During cement job fluid circulated w/o till plug down.</u>					

1st Run 15 jts 1" Tagged @ 465'
pumped 350 sacks class C 3% occ 6:30pm 6/7/78

Last dry break @ 1021'

2nd Run 12 jts 1" Tagged @ 373
pumped 175 sacks class C 3% occ
cement circulated. 3:00AM 6/8/78