

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

RECEIVED

SEP 9 1982

O. C. D.
ARTESIA OFFICE

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Corp.</u>		Lease <u>Bitter Lakes A & St</u>		Well # <u>1</u>	
Location of Well	Unit <u>M</u>	Section <u>16</u>	Township <u>10S</u>	Range <u>25E</u>	County <u>Chaves</u>
Drilling Contractor	<u>AFT #2</u>		Type of Equipment <u>Rotary</u>		

★ WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used <u>conductor</u>	Depth	Sacks Cement
<u>14 3/4"</u>	<u>10 3/4"</u>	<u>40.5 J-55</u>	<u>NEW</u>	<u>80'</u>	
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.5</u>	<u>NEW</u>	<u>TD</u>	<u>600 (CIRC)</u>
					<u>350</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____

(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 14 3/4" Size of Casing 10 3/4" Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 3 jts welded _____

TD of hole 650' Set 500' Feet of 10 3/4" Inch 40.5 # Grade K-55

New used csg. @ 520' with 200 27cc sacks neat cement around shoe
+ 300 sack Western White additives (1/4# celvash, 370cc)

Plug down @ 1215 (AM) (PM) Date 9/2/82

Cement circulated Yes No. of Sacks 255x

Cemented by Western Co. Witnessed by Mick Stillefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Operator had to work casing down from 90'-520'.

Casing was stuck in hole @ 520'.

Full returns to 650'
Last day break @ 617'.

Bot of wth in hole.