

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

| | | | | | |
|--|------------------|--------------------------|---------------------------------|------------------|----------------------|
| Operator <u>Mesa Pet. Co.</u> | | Lease <u>M.E.C. Com.</u> | | Well # <u>1</u> | |
| Location of Well | Unit <u>M</u> | Section <u>6</u> | Township <u>7S</u> | Range <u>23E</u> | County <u>Chaves</u> |
| Drilling Contractor | <u>Tom Brown</u> | | Type of Equipment <u>Rotary</u> | | |
| * Witness | | | | | |
| <u>APPROVED CASING PROGRAM</u> | | | | | |
| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth | Sacks Cement |
| <u>12 1/4"</u> | <u>8 5/8"</u> | <u>24#</u> | <u>New</u> | <u>1400'</u> | <u>Circ</u> |
| <u>7 7/8"</u> | <u>4 1/2"</u> | <u>10.5#</u> | <u>"</u> | <u>3200'</u> | <u>300 Sks.</u> |
| Casing Data: | | | | | |
| Surface _____ joints of _____ inch _____ # Grade _____ | | | | | |
| (Approved) (Rejected) | | | | | |
| Inspected by _____ date _____ | | | | | |
| Cementing Program | | | | | |
| Size of hole _____ Size of Casing _____ Sacks cement required _____ | | | | | |
| Type of Shoe used _____ Float collar used _____ Btm 3 jts welded _____ | | | | | |
| TD of hole <u>1250</u> Set <u>1262</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u> | | | | | |
| New-used csg. @ <u>1262</u> with <u>200</u> sacks neat cement around shoe | | | | | |
| + <u>450</u> <u>450</u> sax <u>BJ Thick Set</u> additives | | | | | |
| Plug down @ <u>10:00</u> (AM) (PM) Date <u>3-22-82</u> | | | | | |
| Cement circulated <u>NO</u> No. of Sacks _____ | | | | | |
| Cemented by <u>BJ</u> Witnessed by _____ | | | | | |
| Temp. Survey ran @ <u>4:00</u> (AM) (PM) Date <u>3-23-82</u> top cement @ <u>620</u> | | | | | |
| Casing test @ _____ (AM) (PM) Date _____ | | | | | |
| Method Used _____ Witnessed by _____ | | | | | |
| Checked for shut off @ _____ (AM) (PM) Date _____ | | | | | |
| Method used _____ Witnessed by _____ | | | | | |
| Remarks: <u>Last Drilling Break 1151</u> | | | | | |
| <u>Tag Cement 68 635</u> | | | | | |
| <u>Run 150 SX Class C 4% CC</u> | | | | | |
| <u>Tag @ 425 Run 50 SX Class C 4% CC</u> | | | | | |
| <u>Tag @ 225 Run 100 SX Class C 4% CC</u> | | | | | |
| <u>Tag @ 125 cement to surface</u> | | | | | |