

NEW MEXICO OIL CONSERVATION CO. DIVISION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Stevens OPR. CO.</u>		Lease <u>Sun Diamond</u>		Well # <u>1</u>	
Location of Well	Unit <u>0</u>	Section <u>20</u>	Township <u>7S</u>	Range <u>26E</u>	County <u>Chaves</u>
Drilling Contractor	<u>HORIZON DRING. CO.</u>		Type of Equipment <u>ROTARY</u>		

* WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>23.0 #</u>	<u>NEW</u>	<u>900'</u>	<u>Circ</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>10.5 #</u>	<u>"</u>	<u>4500'</u>	<u>Circ</u>

Casing Data:

Surface 24 joints of 8 5/8 inch 24 # Grade J-55

yes (Approved) (Rejected)

Inspected by B.W. Weaver date 1-8-83

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 300

Type of Shoe used Tex-Pat Float collar used Insert Btm 3 jts welded yes

TD of hole 900 Set 910 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 910 with 300 sacks neat cement around shoe

+ 4.50 sax 50-50 Pos additives 2% CC

Plug down @ 230 (AM) (PM) Date 1-9-82

Cement circulated yes No. of Sacks 355X

Cemented by Hawco Witnessed by B.W. Weaver

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Last Drilling Break 785