

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>SANDERS OIL & GAS</u>		Lease <u>CANNON ET AL.</u>		Well # <u>1-Y</u>	
Location of Well	Unit <u>N</u>	Section <u>27</u>	Township <u>10S</u>	Range <u>25E</u>	County <u>CHAVES</u>
Drilling Contractor	<u>YOUNG</u>		Type of Equipment <u>ROTARY</u>		

* WITNESS APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>52 #</u>	<u>NEW</u>	<u>350</u>	<u>CIRC.</u>
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>32 #</u>	<u>"</u>	<u>700</u>	<u>CIRC.</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>"</u>	<u>4400</u>	<u>375 SXS.</u>

Casing Data:

Surface joints of inch # Grade
(Approved) (Rejected)

Inspected by date

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required

Type of Shoe used Key-Pat Float collar used Insert Btm 3 jts welded yes

ID of hole 7 1/8 Set 720 Feet of 8 5/8 Inch 32 # Grade J-55

New-used csg. @ 720 with 150 sacks neat cement around shoe
+ 300 sax BJ Life additives

Plug down @ 10.00 (AM) (PM) Date 12-28-82

Cement circulated No No. of Sacks

Cemented by BJ Hughes Witnessed by R. W. Weaver

Temp. Survey ran @ 4:00 (AM) (PM) Date 12-29-82 top cement @ 437

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Ran 1" to 437 cemented with 20 SX Class C 4% CC
Tag @ 396 Ran 230 SX Class C 4% CC
Tag @ 225 Ran 150 SX Class C 4% CC Circ Cement to surface