

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>Spool 50</u>		Well # <u>2</u>	
Location of Well	Unit <u>D</u>	Section <u>23</u>	Township <u>7</u>	Range <u>25</u>	County <u>Chaves</u>
Drilling Contractor	<u>N/A</u>		Type of Equipment <u>Rotary</u>		
* WITNESS <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4"</u>	<u>10 3/4"</u>	<u>48 #</u>	<u>NEW</u>	<u>840'</u>	<u>circ</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>"</u>	<u>TD</u>	<u>350 SX</u>
Casing Data:					
Surface <u>21</u> joints of <u>10 3/4</u> inch <u>40.5</u> # Grade <u>J-55</u>					
<u>yes</u> (Approved) (Rejected)					
Inspected by <u>BW Weaver</u> date <u>4-28-83</u>					
Cementing Program					
Size of hole <u>14 3/4</u> Size of Casing <u>10 3/4</u> Sacks cement required <u>200</u>					
Type of Shoe used <u>Tex-Art</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>840</u> Set <u>843</u> Feet of <u>10 3/4</u> Inch <u>40.5</u> # Grade <u>J-55</u>					
New-used csg. @ <u>843</u> with <u>300</u> sacks neat cement around shoe					
+ <u>400</u> sax <u>BJ Lite</u> additives					
Plug down @ <u>3:15</u> (AM) (PM) Date <u>4-28-83</u>					
Cement circulated <u>No</u> No. of Sacks					
Cemented by <u>BJ Hughes</u> Witnessed by					
Temp. Survey ran @ <u>10:00</u> (AM) (PM) Date <u>4-28-83</u> top cement @ <u>430</u>					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by <u>BW Weaver</u>					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <u>Last Drilling Break 708 Loss Zone @ 440</u>					
<u>Ran 1" Tagged @ 430 Cemented 25 SX class C</u>					
<u>Tag @ 430 Ran 50 SX C 3%</u>					
<u>Tag @ 320 Ran 25 SX C 3%</u>					
<u>Tag @ 240 Ran 50 SX C 3%</u>					
<u>Tag @ 235 Ran 250 SX C 3% fine cement</u>					