

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet Corp.</u>		Lease <u>BLAZER XN ST</u>		Well # <u>1</u>	
Location of Well	Unit <u>C</u>	Section <u>15</u>	Township <u>7</u>	Range <u>23</u>	County <u>CHAVES</u>
Drilling Contractor	<u>LPM</u>		Type of Equipment <u>ROTARY</u>		
* WITNESS APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>1 3/4</u>	<u>10 3/4</u>	<u>40.5</u>	<u>NEW</u>	<u>1100</u>	<u>Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>9.5</u>	<u>"</u>	<u>TD</u>	<u>350</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____ (Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>1 3/4</u> Size of Casing <u>10 3/4</u> Sacks cement required _____					
Type of Shoe used <u>GUIDE</u> Float collar used <u>INSERT</u> Btm 3 jts welded <u>YES</u>					
TD of hole <u>1123</u> Set <u>1127</u> Feet of <u>10 3/4</u> inch <u>40.5</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1123</u> with <u>300</u> sacks neat cement around shoe <u>CLC 3%</u>					
+ <u>100</u> sax <u>THIXOLITE</u> additives <u>1/2 # SK. CBLDFLAK</u> , <u>10 # SK GILSONITE</u> , <u>2% CaCl₂</u>					
Plug down @ <u>10:00</u> <u>(AM)</u> (PM) Date <u>5/21/83</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>WESTERN</u> Witnessed by <u>Harry Brooks</u>					
Temp. Survey ran @ <u>4:00</u> <u>(AM)</u> <u>(PM)</u> Date <u>5/21/83</u> top cement @ <u>350</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: * <u>+400 SXS. PACESETTER LITE 3% CaCl 5 #/SK Gilsonite + 1/4 #/SK cellophane</u>					
<u>1.) TAGGED AT 350', PUMPED 100 SXS. CLC 4% CaCl₂</u>					
<u>TAGGED AT 350', NO FILL, NO FLUID LEVEL ON 1"</u>					
<u>REDI-MIXED TO SURFACE W/ 12 YDS. CMT.</u>					