

730

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Petr Corp</u>		Lease <u>Blazer "XN" St</u>		Well # <u>2</u>	
Location of Well	Unit <u>8605 660W m</u>	Section <u>16</u>	Township <u>7</u>	Range <u>23</u>	County <u>Chaves</u>
Drilling Contractor	<u>AFT #2</u>		Type of Equipment <u>Rotary</u>		
* witness					
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>14 3/4</u>	<u>10 3/4</u>	<u>40.5 #</u>		<u>1100</u>	<u>800 SX Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>9.5 #</u>		<u>3300</u>	<u>350 SY</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>14 3/4</u> Size of Casing <u>10 3/4</u> Sacks cement required _____					
Type of Shoe used <u>Tex-A</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1100</u> Set <u>1146</u> Feet of <u>10 3/4</u> Inch <u>40.5 #</u> Grade <u>J-55</u>					
New-used csg. @ <u>1116</u> with <u>300</u> sacks neat cement around shoe					
+ <u>400</u> sax <u>Pacethite</u> additives <u>100 Phucsolite</u>					
Plug down @ <u>130</u> (AM) (PM) Date <u>8-1-83</u>					
Cement circulated <u>N/C</u> No. of Sacks _____					
Cemented by <u>Western</u> Witnessed by <u>BW Weaver</u>					
Temp. Survey ran @ <u>7:30</u> (AM) (PM) Date <u>8-1-83</u> top cement @ <u>370</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Loss Circulation @ 218 ft</u>					

Ran 1" to 310 ft  
25 SX Class C Tag @ 254  
25 SX Class C Tag @ 213  
25 SX Class C Tag @ 172  
1 25 SX Class C Tag @ 100  
70 SX Class C Circulate to Surface