

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>Rajillo Dr. WQ ST.</u>		Well # <u>5</u>	
Location of Well	Unit <u>E</u>	Section <u>27</u>	Township <u>7</u>	Range <u>23</u>	County <u>Chaves</u>
Drilling Contractor	<u>AFT #2</u>		Type of Equipment <u>ROTARY</u>		
<p>* Witness <u>APPROVED CASING PROGRAM</u></p>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>* 14 3/4</u>	<u>10 3/4"</u>	<u>40.5 J-55</u>	<u>NEW</u>	<u>1100</u>	<u>CIRC.</u>
<u>7 7/8</u>	<u>4 1/2"</u>	<u>9.5 J-55</u>	<u>"</u>	<u>TD</u>	<u>350 SxS.</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>14 3/4</u> Size of Casing <u>10 3/4</u> Sacks cement required <u>200</u>					
Type of Shoe used <u>Tex-Pat</u> Float collar used <u>INSERT</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>1100</u> Set <u>1130</u> Feet of <u>10 3/4</u> Inch <u>40.5</u> # Grade <u>J-55</u>					
New- used csg. @ <u>1130</u> with <u>300</u> sacks neat cement around shoe					
+ <u>100</u> sax <u>Thicksolite</u> + additives <u>400 SX Pace Setter lite 1/2 Flo Sol #5 Gilsomite</u>					
Plug down @ <u>615</u> (AM) (PM) Date <u>8-31-83</u> <u>3% calcium chloride</u>					
Cement circulated <u>No</u> No. of Sacks _____					
Cemented by <u>Western</u> Witnessed by <u>B W Weaver</u>					
Temp. Survey ran @ <u>12:00</u> (AM) (PM) Date <u>8-31-83</u> top cement @ <u>9:25</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Loss zone @ 265</u>					
<u>Run 1" to 530 ft 50 SX Class C 3% CC</u>					
<u>Taq @ 390 Run 50 SX Class C 3% CC</u>					
<u>Taq @ 370 Run 50 SX Class C 3% CC</u>					
<u>Taq @ 325 Run 50 SX Class C 3% CC</u>					
<u>Taq @ 325 Run 50 SX Class C 3% CC</u>					
<u>Taq @ 325 Run 50 SX Class C 3% CC</u>					
<u>Taq @ 325 Ready-Mix to Surface 124d</u>					