

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

9-9-84

Operator <u>Getty Oil Co.</u>		Lease <u>Getty P.S. 17 Fed. Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>H</u>	Section <u>17</u>	Township <u>6</u>	Range <u>26</u>	County <u>Chaves</u>
Drilling Contractor	<u>N/A</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

*** WITNESS**

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
* <u>14 3/4"</u>	<u>10 3/4"</u>	<u>40.5</u>	<u>NEW</u>	<u>920'</u>	<u>CIRC</u>
<u>9 7/8"</u>	<u>7"</u>	<u>20.0</u>	<u>"</u>	<u>1650'</u>	<u>OPTIONAL</u>
<u>7"</u>	<u>4 1/2"</u>	<u>10.5</u>	<u>"</u>	<u>4200'</u>	<u>804 Sxs.</u>

Casing Data:

Surface 23 joints of 10 3/4 inch 45.5 # Grade J-55

Yes (Approved) (Rejected)

Inspected by BW Weaver date 6-26-84

Cementing Program

Size of hole 14 3/4 Size of Casing 10 3/4 Sacks cement required 200

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Yes

TD of hole 889 Set 889 Feet of 10 3/4 Inch 45.5 # Grade J-55

New-used csg. @ 889 with 200 sacks neat cement around shoe

+ 350 sax Hawco lite additives 1/4 Flo Seal 2% CC

Plug down @ 12:15 (AM) (PM) Date 6-27-84

Cement circulated Yes No. of Sacks 90

Cemented by Hawco Witnessed by BW Weaver

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Last Drilling Break 261