

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Exp. 1-13-85

Operator <b>YPC</b>		Lease <b>SAHARA ZV COM</b>		Well # <b>1</b>	
Location of Well	Unit <b>J</b>	Section <b>2</b>	Township <b>9S</b>	Range <b>25E</b>	County <b>CHAVES.</b>
Drilling Contractor	<b>L &amp; M 2</b>		Type of Equipment <b>ROTARY</b>		

**\* = CSG. TO WITNESS**

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<b>* 14 3/4</b>	<b>10 3/4"</b>	<b>40.5</b>	<b>NEW</b>	<b>850'</b>	<b>CIRC</b>
<b>7 7/8</b>	<b>4 1/2"</b>	<b>9.5</b>	<b>"</b>	<b>TD</b>	<b>CIRC</b>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole <sup>14 3/4</sup>~~12 1/4~~ Size of Casing <sup>10 3/4</sup>~~8 1/2~~ Sacks cement required **450**

Type of Shoe used <sup>TPC</sup> Float collar used <sup>inst</sup> Btm 3 jts welded **yes**

TD of hole **830** Set **830** Feet of **10 3/4** Inch **40.5** # Grade **J-55**

**(New)**-used csg. @ **830** with **150** sacks neat cement around shoe circ 3% cc  
+ **300** sax **Face setter lte.** additives **CaCl<sub>2</sub> 3%**

Plug down @ **1130** **(AM)** (PM) Date **7/30/84**

Cement circulated **yes** No. of Sacks **35**

Cemented by **Western** Witnessed by **LB**

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_