

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>C&amp;K Pet Inc</u>		Lease <u>Little Cuervo St</u>		Well # <u>1</u>	
Location of Well	Unit <u>I</u>	Section <u>15</u>	Township <u>17</u>	Range <u>19</u>	County <u>Chaves</u>
Drilling Contractor	<u>1980 FSL &amp; 760 FEL</u> <u>Hondo Drly.</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>65"</u>		<u>120'</u>	<u>circ</u>
<u>12 1/4"</u>	<u>8 5/8"</u>	<u>24"</u>		<u>1500'</u>	<u>circ</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.5 x 10.5</u>		<u>6500'</u>	<u>4000'</u>

Casing Data:

Int  
Surface 49 joints of 8 5/8 inch 24 # Grade API New K-55  
(Approved) (~~Rejected~~)

Inspected by Lelan Merriam date 12-10-74

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8 Sacks cement required 740

Type of Shoe used Guide Float collar used Yes Btm 2 jts welded Thread Lock

TD of hole 1496' KB Set 1485' Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 1485 with 300 sacks neat cement around shoe Class C 2% CC 1/4" Flt. 14.8  
+ 440 sax Howes Lite additives 5# Gilsomite 1/4" Flocc 2% CC 12.8-13.0

Plug down @ 2:30 (AM) (PM) Date 12-13-74

Cement circulated Yes No. of Sacks 50/54

Cemented by Waller to Witnessed by Lelan Merriam

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: 17 1/2 hole TD 114 Set 103 GL' 3 1/2 13 7/8" C/T 115/54

Class C 2% CC PD 12-6-74

Water 180-203 240-64, 1018-23 1050-53

TD 6420 P&P 1-13-75 355x 63 6000 5000-5100 33.3400