

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Phoenix Resources Co.</i>		Lease <i>Buckhorn Canyon</i>		Well # <i>1</i>	
Location of Well	Unit <i>0</i> <i>9905</i> <i>1900e</i>	Section <i>18</i>	Township <i>19</i>	Range <i>20</i>	County <i>Chaves</i>
Drilling Contractor <i>Cactus Drilling Co. #24</i>			Type of Equipment <i>Rotary to start 1-7-78</i>		
<i>J.C. Denny company man</i> <u>APPROVED CASING PROGRAM</u> <i>* Witness</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>48</i>		<i>150</i>	<i>175 circ.</i>
<i>11"</i>	<i>8 5/8"</i>	<i>24</i>		<i>1790</i>	<i>1100 "</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>11.6</i>		<i>7400</i>	<i>500</i>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <i>12 1/4</i> Size of Casing <i>8 5/8</i> Sacks cement required <i>1200</i>					
Type of Shoe used <i>guide</i> Float collar used <i>insert</i> Btm <i>2</i> jts welded <i>yes</i>					
TD of hole <i>1790'</i> Set <i>1793'</i> Feet of <i>8 5/8</i> Inch <i>24</i> # Grade <i>K-55</i>					
New-used csg. @ <i>1773'</i> with <i>200</i> 2% sacks neat cement around shoe					
+ <i>200</i> sax <i>mix set</i> additives <i>270cc</i>					
Plug down @ <i>8:00</i> (AM) (PM) Date <i>1/29/79</i>					
Cement circulated <i>No</i> No. of Sacks _____					
Cemented by <i>Halliburton</i> Witnessed by <i>Mike Stubbins</i>					
Temp. Survey ran @ <i>4:00</i> (AM) (PM) Date <i>1/30/79</i> top cement @ <i>980'</i>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <i>+ 800 sx 50-50 per. (4% gel - 4# floxide - 5# gilsonite - 270cc)</i>					
Centrifuges @ <i>1718'-1753'-1613'</i> Lost returns <i>990'</i>					
Baskets @ <i>1105'-914'</i> Lost dry break <i>1168'</i>					